AD-A167 106 FRACTURE IN STABILIZED SOILS VOLUME 2(U) TEXAS 1/2
TRANSPORTATION INST COLLEGE STATION D N LITTLE ET AL.
31 DEC 85 AFOSR-TR-86-0242-VOL-2 F49620-82-K-0027
UNCLASSIFIED F/G 8/13 NL





MICROCOPY CHART

(2)

FRACTURE IN STABILIZED SOILS

VOLUME 2

FINAL TECHNICAL REPORT

DECEMBER 31, 1985

Prepared for
Texas A&M University
and the Air Force Office of Scientific Research

Prepared by
The Texas Transportation Institute

The Texas A&M University System
College Station, Texas

Unclassified
URITY CLASSIFICATION OF THIS PAGE

AD-A167106

REPORT DOCUMENTATION PAGE

REPORT SECURITY CLASSIFICATION: Unclassified	1b. RESTRICTIVE MARKINGS
SECURITY CLASSIFICATION AUTHORITY	3. DISTRIBUTION/AVAILABILITY OF REPORT: Approved for public release; distribution unlimited.
DECLASSIFICATION/DOWNGRADING SCHEDULE	
PERFORMING ORGANIZATION REPORT NUMBER(S)	5. MONITORING ORGANIZATION REPORT NUMBER(S): AFOSR-TR- 86-0242
NAME OF PERFORMING ORGANIZATION: Texas A&M University Texas Transportation Institute; 6b. OFFICE SYMBOL (If applicable)	7a. NAME OF MONITORING ORGANIZATION: Air Force Office of Scientific Research
ADDRESS (City, State and ZIP Code): College Station, Texas 77843	7b. ADDRESS (City, State and ZIP Code): Bolling AFB, DC 20332
NAME OF FUNDING/SPONSORING ORGANIZATION: Office of Scientific Research; 8b. OFFICE SYMBOL (If applicable): NA	9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER: F49620-82-K-0027
ADDRESS (City, State and ZIP Code): Bolling AFB DC 20332-6448	10. SOURCE OF FUNDING NOS.

PROGRAM ELEMENT NO.	PROJECT NO.	TASK NO.	WORK UNIT NO.
61102F	2302	C2	

TITLE (Include Security Classification): Fracture in Stabilized Soils - Vol 1 & 2

PERSONAL AUTHOR(S): D. N. Little, W. W. Crockford, and Y. Kim

13a. TYPE OF REPORT	13b. TIME COVERED	14. DATE OF REPORT (Yr., Mo., Day)	15. PAGE COUNT
Final Technical	FROM 820401 TO 851231	851231	300

16. SUPPLEMENTARY NOTATION

17. COSATI CODES			18. SUBJECT TERMS (Continue on reverse if necessary and identify by block number)
FIELD	GROUP	SUB. GR.	
			Fracture Mechanics

19. ABSTRACT (Continue on reverse if necessary and identify by block number)

Conventionally the thickness design of stabilized soil layers has been based upon the tensile strength of the stabilized soil layer and/or the appearance of the first crack. The design literature does not allow one to consider the true development of cracking in the stabilized soil layer. Knowledge of the mode of such cracking could drastically alter the philosophy behind thickness design of layers.

In this research the principles of theoretical fracture mechanics are used to explain the mode and mechanism of fracture in fine grained media stabilized with portland cement. Experimental fracture mechanics is used to validate or verify and in some cases to investigate more fully the hypothesized mechanisms of fracture. The influence of osmotic and matrix soil section, temperature, binder content, thermal and kinetic energy, from sources outside the crack, are considered in the study.

Linear elastic fracture mechanics is proven to be a highly acceptable analytical tool for these materials.

20. DISTRIBUTION/AVAILABILITY OF ABSTRACT	21. ABSTRACT SECURITY CLASSIFICATION
UNCLASSIFIED/UNLIMITED ☐ SAME AS RPT. ☐ DTIC USERS ☐	Unclassified

22a. NAME OF RESPONSIBLE INDIVIDUAL	22b. TELEPHONE NUMBER (Include Area Code)	22c. OFFICE SYMBOL
LAWRENCE D. HOKANSON	(202) 767-4935	NA

DD FORM 1473, 83 APR EDITION OF 1 JAN 73 IS OBSOLETE.

TABLE OF CONTENTS

TABLE OF CONTENTS continued

LIST OF TABLES

LIST OF FIGURES

LIST OF FIGURES (cont.)

CHAPTER I: INTRODUCTION

Purpose

The purpose of this research is to establish a preliminary model to investigate the crack propagation history in a given pavement system. This is accomplished through a multi-step process. First, a suitable program is used to calculate the stress distribution in the pavement layers under the load, in this study an elastic layer program. Second, through successive application of a finite element program, the stress intensity factor as a function of crack length is determined. Third, using the stress intensity factor distribution, the number of load cycles required to advance the crack a given increment is calculated. These increments carry the crack from its initial to its final value, which defines failure. The load cycles are calculated using the Paris equation. The remainder of the report is taken up by a detailed description of the problem and an in-depth account of the solution process and results.

Pavement System

The pavement system used in this study consists of a combination of three layers: a subgrade, a base, and a surface. Each layer has variable values for the modulus of elasticity and the thickness. This information is summarized in Table 1.

The subgrade thickness is listed as 50 inches. This is an arbitrary value selected so that the subgrade thickness does not affect the solution.

Table 1. Pavement Data Used in Developing Structural Data.

LAYER	MODULUS VALUES,PSI	THICKNESSES,IN.	POISSON'S RATIO
overlay	350000.0	0 3 6	0.35
base	400000.0 800000.0 1200000.0	8 12 16	0.35
subgrade	4000.0 9000.0	50	0.35

MODULUS CONDITIONS

MODULUS CONDITION	BASE MODULUS,PSI	SUBGRADE MODULUS,PSI
1	1200000.0	4000.0
2	1200000.0	9000.0
3	800000.0	4000.0
4	800000.0	9000.0
5	400000.0	4000.0
6	400000.0	9000.0

In the analysis of the pavement system, all possible combinations of the values in Table 1 are used to develop the influence of pavement properties on fracture.

Loading

The loading shown in Figure 1 approximates that of an F-4 aircraft. It consists of a total load of 27,000 pounds. This load is distributed over a circle with a radius of 5.7 inches to provide a pressure of 265 psi.

Solution Philosophy

Strictly speaking, this problem is a three dimensional axi-symmetric one. However, because crack propagation itself is generally a plane strain phenomenon, it is considered preferable to rely on a simpler solution scheme. The approach here is to use a two-dimensional plane strain finite element program to obtain approximate stress intensity factors developing under the stresses calculated from an elastic layer analysis. for a single load, as assumed here, the results are satisfactory.

The cornerstone of the solution procedure is the computation of the stress intensity factor as a function of crack length. This is done with the finite element program described in a later chapter and with the aid of superposition techniques. When dealing with boundary values over an infinite region such as a pavement structure, the problem can be analyzed as the superposition of two problems (1) as illustrated in Figure 2. In the first phase, one applies the total loading to the pavement with no crack. For the second phase, the crack is included in the pavement. The stresses where the



Figure 1. Loading Condition Modelled With Finite Element Fracture Program.



Figure 2. Schematic of Superposition Principle to Solve for Stress Intensity on Crack

crack would be in the first phase are applied in the reverse direction to the crack in the second phase. The stress intensity factor found from the second phase, although of opposite sign, is equal in magnitude to that of the overall problem. Thus the task of finding K_I becomes one of discovering the correct stress distribution due to loading at the crack, applying the reverse stresses to the crack, and analyzing the pavement.

A further difficulty arises when using the above superposition. As will be noted, stresses cannot be applied to the portion of the crack which lies within the crack tip finite element. Thus, a correction factor is required to account for this. The correction factor is given by (1) as:

$$C_k = \frac{\sqrt{2}}{\pi} \int_0^z \frac{\sigma_e(\S)\, d\S}{\sqrt{\S}} \qquad (1)$$

where $\S$ is the distance away from the crack tip and $\sigma_e(\S)$ is the stress to be applied to the portion of the crack that lies within the crack element. If z is sufficiently small, $\sigma_e(\S)$ can be assumed to be a constant, and equation (1) reduces to (1):

$$C_k = \left(\frac{8}{\pi}\right)^{1/2} \sigma_e \sqrt{2} \qquad (2)$$

The final, correct stress intensity factor is found from C_K and K_I computed in superposition phase two by

$$K_{I\ final} = K_{I\ computed} + C_K \qquad (3)$$

Crack propagation is calculated using this stress intensity factor in

numerical integration of the Paris equation. The Paris equation consists of the following:

$$dc/dN = AK_I^n \tag{4}$$

where

dc = differential crack extension

dN = differential increase in the number of load cycles

K_I = stress intensity factor

A,n = dimensionless material constants determined experimentally

Manipulation of the Paris equation gives:

$$dN = dc/AK_I^n \tag{5}$$

from which ΔN_f, the number of load cycles required to advance the crack an increment can be calculated as:

$$\Delta N_f = \int_{c_o}^{c_f} \frac{dc}{A\ K_I^n} \tag{6}$$

Writing the integral in terms of c/b leaves:

$$\Delta N_f = b \int_{(c/b)_o}^{(c/b)_f} \frac{d(c/b)}{A\ K_I^n} \tag{7}$$

When the current crack length equals the crack length at failure, the final value of N_f is reached.

The total number of load cycles required to advance the crack from the initial crack length to the current crack length, N_{fn}, is found by summing the ΔN_f values for the n crack increments which total the current crack length. Thus,

$$N_{fn} = \sum_{1}^{n} \Delta N_{fn} = N_{f(n-1)} + \Delta N_{fn} \tag{8}$$

Note that K_I is considered a function of (c/b) now, not crack length. This allows regression equations to be developed for the range of materials and loading conditions which lessens the reliance on the finite element computer code.

In this analysis the crack is assumed to form directly beneath the center line of the load, on the line of symmetry. It is assumed to originate at the interface of the base and the subgrade and to propagate upward through the base. The greatest crack length at which the pavement is assumed to have failed is the full thickness of the base. If c = crack length in the base and b = thickness of the base, then c/b = 1.0 is the maximum value at which failure can occur. This would lead one to believe that the life of the pavement ranges between c/b values of 0.0 and 1.0. However, this is true only if two conditions exist. First, K_I, the stress intensity factor, must be positive for all c/b. Second, the critical value of the stress intensity factor, K_{IC}, must not be exceeded. In the first case, if K_I is negative, then the crack cannot propagate in that region and that region cannot figure in the fracture life of the pavement. The areas defining the fracture life of the pavement when K is negative are illustrated in Figure 3, where typical K_I distributions for this problem are depicted. Case I and II are self-explanatory. In case III, it is assumed that some perturbation advances



Figure 3. Schematics of Possible Stress Intensity Factor Distributions

the crack to $(c/b)_1$, so that the crack can propagate. Here $(c/b)_1$ is considered small so that this is readily possible and handled with the concept of starter flaws. If $(c/b)_1$ is not small, then the crack may never propagate. In case IV, the crack propagates to $(c/b)_1$ in the normal fashion and once there encounters negative K_I values and stops. It is unlikely that the crack will somehow be advanced suddenly through the relatively extensive negative K_I region, and if it is, the pavement will be nearly destroyed and can be said to have failed. Thus $(c/b)_1$ is the upper limit of the fatigue life in this case. One should note that if $(c/b)_1$ is significantly less than 1.0, then exhausting the fatigue life may not constitute failure of the pavement. The pavement may still maintain its structural integrity.

If K_{IC} is exceeded, then the crack instantly propagates to a point where $K_I = K_{IC}$. The fatigue life would then range between c/b values where K_I is less than or equal to K_{IC}. If K_I never falls below K_{IC} again, then the crack instantly propagates to failure. Unfortunately, K_{IC} values for the pavements in this problem are unknown, so there is no way to incorporate them into the solution algorithm. Therefore, for purposes of analysis, it is assumed that K_{IC} is greater than K_I for all c/b.

Solution Sequence

the solution sequence briefly described here will be described in detail in the following chapters. The stress distribution calculations will not be described, as this program can be replaced with any program which calculates stresses and strains under a loading. Other elastic theory programs can be used which will allow multiple wheel loadings to be used to produce the

stress distribution which is then used in the finite element fracture program. The Hybrid crack tip element of Pian and Tong used in a plane strain finite element program is used to determine the stress intensity factors resulting when a cracked base course is subjected to the calculated stress distribution. Regression equations have been developed in this study to reduce the use of the finite element program for simple pavement structures. Finally, the Paris equation is used in a program to calculate the number of loads to failure under the given stress intensity distribution.

CHAPTER II: THE FINITE ELEMENT PROGRAM

The Singularity Problem

For linearly elastic plane strain and plane stress problems, in the vicinity of a crack tip the stress varies as $1/\sqrt{r}$, where r is the radial coordinate of any point in the plane measured from the crack tip. Thus, at the crack tip where r = 0 the stress is singular. In the equations for stress, the coefficient of the singular $1/\sqrt{r}$ term is called the stress intensity factor and is representative of the "strength" of the singularity. It has units of (force/area)* $\sqrt{\text{length}}$. There are two main types of crack which govern the behavior of linearly elastic plane stress/strain problems. These are:

1) mode I or opening mode

2) mode II or in-plane shearing

These modes are illustrated in Figure 4.

For isotropic materials, the singular terms of the stress distribution in the vicinity of a crack tip are (3):

mode I:

$$\{\sigma\} = \begin{Bmatrix} \sigma_x \\ \sigma_y \\ \sigma_{xy} \end{Bmatrix} = \left(K_I \sqrt{2\pi r}\right) \begin{Bmatrix} \cos(\theta/2)[1 - \sin(\theta/2)\sin(3\theta/2)] \\ \cos(\theta/2)[1 + \sin(\theta/2)\sin(3\theta/2)] \\ \sin(\theta/2)\cos(\theta/2)\cos(3\theta/2) \end{Bmatrix} \qquad (8)$$

mode II:

$$\{\sigma\} = \begin{Bmatrix} \sigma_x \\ \sigma_y \\ \sigma_{xy} \end{Bmatrix} = \left(K_{II} \sqrt{2\pi r}\right) \begin{Bmatrix} -\sin(\theta/2)[2 + \cos(\theta/2)\cos(3\theta/2)] \\ \sin(\theta/2)\cos(\theta/2)\cos(3\theta/2) \\ \cos(\theta/2)[1 - \sin(\theta/2)\sin(3\theta/2)] \end{Bmatrix} \qquad (9)$$

In many formulations, the coefficient involving K in front of the vectors containing trigonometric terms in equations (8) and (9) is given as $(K/\sqrt{2r})$. The finite element program used in this research uses equations (8) and (9) as is. With the use of these equations it is necessary to multiply the results of the finite element program by $\sqrt{\pi}$ in order to match any results obtained from stress distributions based on the alternative coefficient. It is a minor point but mix-up in definitions can lead to confusion and incomprehensible results.

The stress intensity factors K_I and K_{II} are directly proportional to the magnitude of applied loading and are dependent on the geometry of the structure, the size and shape of the crack, and the nature of the applied loading.

Displacement fields in the vicinity of a crack tip are also functions of the stress intensity factors and can be written as :

mode I:

$$\begin{bmatrix} u \\ v \end{bmatrix} = \left(K_I \sqrt{\frac{2r}{\pi}}\right)/8G \begin{bmatrix} (2K - 1)\cos\theta/2) - \cos(3\theta/2) \\ (2K + 1)\sin(\theta/2) - \sin(3\theta/2) \end{bmatrix} \qquad (10)$$

mode II:

$$\begin{bmatrix} u \\ v \end{bmatrix} = \left(K_{II} \sqrt{\frac{2r}{\pi}}\right)/8G \begin{bmatrix} (2K + 3)\sin(\theta/2) + \sin(3\theta/2) \\ -(2k - 3)\cos(\theta/2) - \cos(3\theta/2) \end{bmatrix} \qquad (11)$$

In equations (10) and (11), u and v are the displacements along the x and y axes in Figure I-1, G is the shear modulus, $k = (3 - 4\nu)$ for plane strain and $(3 + \nu)/(1 + \nu)$ for plane stress, and ν is Poisson's ratio.

The stress intensity factor is also related to the strain energy release rate, that is the change in strain energy in the structure per unit distance of crack extension. For linearly elastic plane strain/stress problems the strain energy release rate is given by (3):

mode I:

$$\mathcal{L}_I = K^2_I(k + 1)/8G \tag{12}$$

mode II:

$$\mathcal{L}_{II} = K^2_{II}(k + 1)/8G \tag{13}$$

where k and G are as defined previously.

The computer program provides for the calculation of the stress intensity factor in two ways. The first and far more emphasized way is to utilize eqs. (8)-(11) and solve for the stress intensity factor directly. The second method is to run the program twice, the second time with a slightly longer crack, note the difference in strain energy, and apply equation (12) and (13). This option is there if the analyst wants to take advantage of it, but it is not the main thrust of the program and is limited in that if both mode I and mode II are present equations (12) and (13) are not applicable.

The justification for using elements with assumed stress and displacement distributions that have the $1/\sqrt{r}$ singularity built in is based on the convergence rate of problems with singularities. The convergence of such problems has been shown to be of order h, where h is the maximum size of the elements used in the solution. The convergence rate is independent of p, the order of the complete polynomial used in the interpolation functions for stress and displacement. The quantities for which the convergence rate was established are the strain energy U and the stress intensity factors K_I and K_{II}. Given the above, in order to achieve good results for U or K using elements without singularities built in, the number of elements needed



Mode I



Mode II

Figure 4. Two Major Modes of Fracture Analyzed in Finite Element Fracture Program.

becomes impractical because results for relatively large h are highly inaccurate. This is the value of solutions using elements with singularities in the region around the crack tip. Although they converge no faster, for relatively large element sizes they give acceptable results. Indeed, making the elements that include singularities too small can have an adverse effect on the results. This peculiarity occurs for this reason. If the elements containing singularities are small enough, the region in the structure significantly affected by the crack will extend beyond the scope of the singular elements and cause errors in adjacent non-singular elements. In the limit of mesh refinement, as all element sizes go to zero, the beneficial effects of elements with singularities disappear, leaving only a solution based on conventional elements.

The Crack Element

The crack element first developed by Pian and Tong (3), and which is shown in Figure 5 is the element used in the finite element program. It must be of sufficient size to insure good results, as mentioned above. The crack element is developed using a functional and methods which are a combination of both assumed stress and displacement models. As such, in this development, internal stresses and displacements as well as boundary displacements and tractions can be assumed independently. The necessary equilibrium and compatibility requirements are incorporated into the Euler equations, which result from the stationary condition of the functional. The Euler equations can be satisfied either exactly or in a average sense, the latter condition being the source of approximation in the finite element method.



Symmetric Element



General Element

Figure 5. Crack Tip Elements

In the previous section a $\sqrt{r}$ term is included in the equations for displacements. It is not desirable to introduce this term into the assumed boundary displacements, for two reasons. First, it can be incorporated into the assumed internal displacements. Second, one of the virtues of this crack element is that it can be used in conjunction with conventional finite elements, and if a $\sqrt{r}$ term were included in its boundary displacement, boundary compatibility between it and a conventional element could not be insured. Of course, insuring this compatibility causes internal and boundary displacements for the crack element to be incompatible, a source of error.

The functional used in this development is, for plane problems,

$$\pi_m = \int_{\partial A_m} (\tilde{U}_i - U_i) T_i \, ds - \int_{S\sigma_m} U_i T_i \, ds + \frac{1}{2} \int_{A_m} [\sigma_{i_j} (U_{i,j} + U_{j,i}) - C_{ijk\ell} \sigma_{ij} \sigma_{K\ell}] \, dA \quad (14)$$

where

A_m = area of the m^{th} element

∂A_m = the boundary of A_m

S_m = the portion of ∂A_m over which tractions are prescribed

S_u = the portion of ∂A_m over which displacements are prescribed

$C_{ijk\ell}$ = the elastic compliance tensor

u_i = a smooth internal displacement field

$\tilde{u}_i$ = assumed boundary displacements

$\bar{u}_i$ = prescribed boundary displacements

T_i = assumed boundary tractions

$\bar{T}_i$ = prescribed boundary tractions

$\tilde{u}_i$ is assumed such that $\tilde{u}_i$ equals $\bar{u}_i$ on S_u. Note that the thickness t is absent from equation (14) as unity is assumed, but can be multiplied in if the thickness is variable variable.

The Euler equations for the functional in equation (7) are

$$\frac{1}{2}(U_{i,j}+U_{j,i})=C_{ijK\ell}\sigma_{K\ell} \quad \text{in Am} \quad (15a)$$

$$\sigma_{ij,j}=0 \quad \text{in Am} \quad (15b)$$

$$J_i=\sigma_{ij}\nu_j \quad \text{on Am} \quad (15c)$$

$$U_i=\tilde{U}_i \quad \text{on Am} \quad (15d)$$

$$T_i=\overline{T}_i \quad \text{on m} \quad (15e)$$

Note that the body force is excluded for simplicity, and that ν_j is a direction cosine.

Equation (15a) represents compliance with stress-strain laws by assumed stresses and displacements, equation (15b) represents the satisfaction of internal equilibrium, equation (15c) represents compatibility of assumed stresses and boundary tractions, equation (15d) represents compatibility of internal and boundary displacements, and equation (15e) represents satisfaction of boundary conditions by boundary tractions. The crack element provides for internal equilibrium and compatibility, interelement compatibility, and boundary conditions on displacements identically. The exact solution satisfies all the Euler equations. Also, if the solution is exact, then the stationary condition on equation (14) will provide for interelement equilibrium and compatibility. Otherwise, interelement equilibrium is satisfied only in a work equivalent sense, while interelement compatibility will be satisfied by assuming the same boundary displacement functions for all elements, crack or conventional.

The element stiffness matrix, whose development is discussed in the following pages, is derived using complex variable techniques.

To begin with, let $z=x+iy$, where x and y are as depicted in Figure 4. As shown previously, $(\sigma) \sim 1/\sqrt{r}$ & $\binom{u}{v} \sim \sqrt{r}$, so that stresses and displacements can be expressed as (3):

$$\left.\begin{aligned} \sigma_y+\sigma_x &= 2[\phi'(z)+\overline{\phi'(z)}] \\ \sigma_y-\sigma_x+2i\sigma_{xy} &= 2[\bar{z}\phi''(z)+\chi'(z)] \end{aligned}\right\} \tag{16}$$

$$2\mu(U+iV)=\eta\phi(z)-z\overline{\phi'(z)}-\overline{\psi(z)} \tag{17}$$

where $\mu = E/2(1+\nu)$, $\eta = 3-4\nu$ for plane strain and $(3-\nu)/(1+\nu)$ for plane stress. E and ν are Young's modulus and Poisson's ratio, respectively. It can be seen that $\mu = G$ and $\eta = k$ in Section I. $(\ )'$ denotes differentiation and $\overline{(\ )}$ denotes the complex conjugate. ϕ and ψ are analytic functions. The above definitions of stress and displacement satisfy Euler equations (15a) and (15b). In addition, boundary tractions are chosen in this development so that they satisfy equation (15c).

In order to choose proper stresses and displacements for the crack element that account for singularities of all order, the following mapping function is introduced (4).

$$z = w(\zeta) = \zeta^2 \tag{18}$$

or

$$\zeta = z^{1/2} \tag{19}$$

with $-\pi/2 \leq \arg \zeta \leq \pi/2$ and $-\pi < \arg z \leq \pi$. On the ζ plane, the element lies on the region where the real part of ζ is positive and the crack lies on the imaginary axis. ϕ and ψ are analytic functions of ζ, enabling simple polynomials in terms of ζ to be used in the finite element solution.

Using the mapping given above, equations (16) and (17) become

$$\sigma_x+\sigma_y=4R_e[\phi'(\mathfrak{L})/w'(\mathfrak{L})]$$

$$\sigma_x+\sigma_y-2i\sigma_{xy}=2\{\overline{w(\mathfrak{L})}[\phi'(\mathfrak{L})/w'(\mathfrak{L})]'+\psi'(\mathfrak{L})\}/w'(\mathfrak{L}) \qquad (20)$$

$$2\mu(+iv)=\eta\phi(\mathfrak{L})-w(\mathfrak{L})\sigma'(\mathfrak{L})/w'(\mathfrak{L})-\psi(\mathfrak{L})$$

In order to satisfy the stress free condition on the crack tip given by (3).

$$\sigma(\mathfrak{L})+w(\mathfrak{L})\overline{\phi'(\mathfrak{L})/w'(\mathfrak{L})}+\overline{\psi(\mathfrak{L})}=0 \qquad (21)$$

the following form of ψ is chosen

$$\psi(\mathfrak{L})-\overline{\phi(-\mathfrak{L})}-\overline{w(-\mathfrak{L})}\phi'(\mathfrak{L})/w'(\mathfrak{L}) \qquad (22)$$

By using equations (15c), (19), (20), and (22) all of the Euler equations except for equation (15d) are satisfied by this crack element model. Substituting equations (21) into (14) gives in matrix form (4):

$$\pi_m=\int_{\partial A_m}(T)^T(\tilde{U})ds-\int_{\partial A_M}(T)^T(U)ds \qquad (23)$$

in which

$$(T)=\begin{bmatrix}T_1\\T_2\end{bmatrix}=\begin{bmatrix}\sigma_x\nu_x+\sigma_{xy}\nu_y\\\sigma_{xy}\nu_x+\sigma_y\nu_y\end{bmatrix}=\text{boundary tractions}$$

$$(u)=\begin{bmatrix}u\\v\end{bmatrix}=\text{internal displacements} \qquad (24)$$

$$(\tilde{u})=\begin{bmatrix}\tilde{u}\\\tilde{v}\end{bmatrix}=\text{boundary displacements}$$

For the derivation of the element stiffness matrix, the following forms of $\phi(L)$ and $\psi(\mathfrak{L})$ may be assumed: (4)

$$\phi(\zeta) = \sum_{j=1}^{N} b_j \zeta_i$$

$$\psi(\zeta) = -\sum_{j=1}^{N} [\bar{b}; (-i)^{j+\frac{j}{2}} b_i] \zeta_i \qquad (25)$$

where N is a finite integer and $b_j = \beta_j + i\,\beta_{N+j}$ with the β's being real constants and $\beta_{N+2} = 0$. This is because $\phi = i^2$ and $\psi = 0$ give no contribution to the stresses in equations (20).

Using equations (20), (24), and (25) one can express the following: (3)

$$(T) = [R](\beta) \qquad (26)$$

$$(u) = [U](\beta)$$

where (β) includes components β_1, β_2,...., β_{2N} excluding β_{N+2}. The boundary displacements ($\tilde{u}$) are expressed as

$$(\tilde{u}) = [L](q) \qquad (27)$$

(q) is the vector of nodal displacements and [L] is an interpolation matrix defined on ∂A_m. [L] is such that boundary displacements for the crack element and adjacent conventional elements are the same. For instance, if, as in the finite element program, linear boundary displacements are employed, then between any two nodes on the crack element [L] will be such that ($\tilde{u}$) has a linear variation.

The number of nodes in the crack element used in the finite element program varies from 5 to 9 depending on symmetry, as shown in Figure 5. Boundary displacements are not assumed along the crack edge of the element because tractions are zero and there is no adjacent element. Because of this, in the program, there is no way to load the portion of the crack within the element and there is no way to control the crack's displacement within the element.

Substitution of equations (26) and (27) into equation (23) gives

$$\pi_m = (\beta)^T [G](q) - 1/2 (\beta)^T [H](\beta) \qquad (28)$$

in which

$$[G] = \int_{\partial Am} [R]^T [L] ds \tag{29}$$

$$[H] = 1/2 \int_{\partial Am} ([R]^T [U] + [U]^T [R]) ds \tag{30}$$

As the β's can be assumed independently from surrounding elements, the stationary condition of equation (28) with respect to (β) gives

$$[H](\beta) = [G](q) \tag{31}$$

or

$$(\beta) = [H]^{-1} [G](q) \tag{32}$$

With equation (31), one can substitute back into equation (28) and eliminate (β). One does not have to. Instead, one could solve for (β)'s simultaneously with the (q)'s. However, in the finite element program the (β)'s are eliminated.

Substituting equation (32) into equation (28) gives (3)

$$\pi_m = 1/2(q)^T [k](q) \tag{33}$$

where the element stiffness matrix for the crack element is

$$[k] = [G]^T [H]^{-1} [G] \tag{34}$$

After global assembly and solution for the global displacement vector, the stress intensity factors can be found from the now known (q). The stress intensity factors can be shown to be related to (β) in the following manner: (4)

$$K_I = (\beta_1)\sqrt{2}$$

$$K_{II} = (\beta_{N+1}) \sqrt{2} \tag{35}$$

Because (β) is related to (q) by equation (32), one can write

$$K_I = (B_I)^T(q)$$

$$K_{II} = (B_{II})^T(q) \tag{36}$$

It appears that $(B_I)^T$ is the first row of $[\ H\ ]^{-1}[\ G\ ]$ multiplied by $\sqrt{2}$ and that $(\ B_{II})^T$ is the $(N+1)^{th}$ row of $[\ H\ ]^{-1}[\ G\ ]$ multiplied by $\sqrt{2}$ as is shown in the program.

The reference followed in the development of this chapter gives details as to how the integrations implied by equations (29) and (30) are to be accomplished in terms of complex variables, and it gives certain properties of [H] (namely that its upper right and lower left quadrants are blocks of zeros) that make it more efficient to invert (4).

The finite element program uses the crack element of the previous section in conjunction with CST triangular elements and 4-CST quadrilateral elements obtained by condensing the middle node. In fact, the program is essentially the program in Desai and Able's finite element text (2) modified to incorporate the crack element.

A complete discussion of the entire program and its input requirements is given in Appendix B.

Operational Parameters

It is convenient to define certain parameters which are used to describe and discuss the crack element. The first parameter is ε .

ε =(Length of crack within crack element)/(Total Crack Length)= a/c

The second parameter is the ratio a/l.

a/l =(Length of crack within crack element)/(Length of Crack Element)

The last parameter is the ratio c/b.

c/b =(Total crack length)/(Depth of Base)

The element shown in Figure 6 is used for all the finite element meshes in the solution procedure yet to be described. Because of the symmetry of the problem, the five node element is used here. It is desirable to use one element for all the meshes so that one can create and build meshes quickly and easily. This particular element is chosen for various reasons. First, it gives a reasonable value of a/l for all c/b ratios. A plot of a/l versus percent error in K_I is shown in Figure 7 for the crack element applied to the Bowie crack problem (5). The above element has a constant a/l ratio of 0.5. It is seen that this a/l ratio yields about a 3 percent error, which is relatively small.

A second reason that the element of Figure 6 is used is that that as the crack propagates, ε remains within reasonable limits for accuracy. This can be seen from Figure 8, which is a plot of ε versus K_I for the Bowie crack problem (5). The element used in this research is the $_2$ element. From this plot, a value of $\varepsilon > 0.2$ is needed to insure reasonable accuracy in K_I. In the solution process for the problem of this report, a maximum value of c/b of 1/2 is used, and a minimum c/b value of 1/12 is used. Also, the greatest b value is 16 inches, and the least is 8 inches. Thus, c_{max} is 8 inches, and c_{min} is 2/3 inches. ε is therefore such that $0.03125 < \varepsilon < 0.375$, and within the range of acceptable accuracy shown in Figure 8.

The above two reasons for using the element shown in Figure 6 are important, but many elements which satisfy the a/l and criteria could be created. The main reason to use the Figure 6 element is that it is small enough so that reverse stresses can be applied to enough of the crack length to make the solution process viable. For instance, c_{min} is 2/3 inches.



Figure 6. Crack Tip Element Used in Analyses



Figure 7. Illustration of Errors Produced By Variation in Crack Tip Length Within The Element (4)



Figure 8. Illustration of Accuracy Related to Crack Tip Length (4)

With a = 1/4 inches, as in Figure 6, one can apply tractions to 5/12 inches, or 62.5%, of the crack length. Remember, one cannot apply tractions to the portion of the crack within the crack element. The 62.5% value can be considered to be a significant amount and meaningful results can be obtained from it. However, as a increases, this percent value decreases and quickly becomes insignificant. If a = c, or ε= 1, then there is no crack length available to apply reverse stresses to, and the solution philosophy outlined earlier 1 is impossible.

There will be five values of c/b used in the finite element analysis of each combination of base, overlay, and modulus. These are shown in Table 2. These values were chosen for accuracy, uniformity, and from an initial study that c/b < 1/2 was the most critical range. Concerning accuracy, it was seen above that c/b = 1/2 produced a maximum c for the 16 inch base of 8 inches and a minimum ε of 0.03125, which is very near the limit for accuracy of 0.02. Actually, the absolute greatest value of c possible is 16 inches in the 16 inch base, and for the element of Figure 6 this corresponds to an ε of 0.015625, which is quite close to 0.02. Therefore, accuracy is not a compelling reason to keep c/b less than 1/2, although for c/b greater than 1/2 one approaches the ragged edge of accuracy.

The uniformity criteria is mainly for convenience. For purposes of comparing trends in K_I distributions from one base-overlay combination to another, it is very helpful to have results computed for the same or similar c/b values. The differences seen in Table 2 for the 12 inch base are because of ease in mesh creation.

The main reason why c/b < 1/2 values are used is that is was thought that they were the most critical values, especially those < 1/6. This thought

Table 2. C/B Values Used in Analylsis

BASE, IN	C/B VALUES
8, 16	1/12, 1/8, 1/6, 7/16, 1/2
12	1/12, 5/36, 1/6, 5/12, 1/2

arose from intuition and previous experience, and is not necessarily borne out by the results in Chapter III.

Other details concerning the element in Figure 6 should be addressed. In Figure 6, the side opposite the crack is straight. For other problems, like the Bowie crack problem, better results are obtained if the side is humped, as in Figure 9. For this problem, however, results using the humped element were poor. Thus the straight side is strongly recommended for this problem. Also, note that in Figure 6 an offset appears at the bottom of the element. This is to simulate the physical opening of the crack. For convenience, this offset is present all the way through the subgrade.



Figure 9. Example of a "Humped" Crack Tip Element

CHAPTER III: SOLUTION PROCEDURE

Development of Stress Distributions

The first step in the solution process is the calculation of the stress distributions to be used in superposition phases discussed in Chapter I. In this problem there is no crack, and thus the finite element program with no crack element can be used to calculate the stress distribution. A distribution must be found for each combination of base thickness, overlay thickness, and modulus to be analyzed. The following combinations are analyzed in this study: all modulus conditions for all base thicknesses with no surface, and all modulus conditions for a base thickness of 8 inches and surfacing of 3 and 6 inches. This information is summarized in Table 3. These specific combinations are analyzed so that all base thicknesses for a given surface (0 inches) can be compared, and all surfaces for a given base thickness (8 inches) can be compared. A sample mesh is shown in Figure 10 for reference. In this mesh, the base thickness is equal to 8 inches and the overlay thickness is 3 inches. The input corresponding to this mesh is listed in Appendix B, along with the corresponding output file. Note that the different modulus conditions can be achieved by simply changing the input values. Also note that the thickness of the meshes in this section is one inch, allowing the 270 psi load to be applied as a traction of the same magnitude.

The results are shown in Table 4. The numbers in the headings are element numbers, and correspond to the elements in the base, along the line of symmetry, where the cracks would run. Lower element numbers refer to elements at the bottom of the base, while higher numbers refer to elements at



Figure 10. Finite Element Mesh Used for Pavement Structural Analysis

Table 3. Pavement Parameters Used in the Factorial Analysis

BASE, IN	SURFACE	MODULUS CONDITIONS
8	0 3 6	1-6
12	0	1-6
16	0	1-6

Table 4. Stress Distributions for Superposition Phase one, psi

8 inch base, no overlay

MC	266	285	304	323
1	1705.1	546.4	-584.5	-1772.1
2	1229.7	383.75	-438.09	-1314.2
3	1455.1	461.01	-507.06	-1530.6
4	1032.3	315.74	-378.84	-1126.6
5	1086.8	334.56	-395.06	-1178.2
6	751.6	218.24	-297.81	-864.87

12 inch base, no overlay

MC	266	285	304	323	342	361
1	1205.5	704.01	234.94	-230.70	-725.58	-1279.1
2	942.39	545.64	178.77	-185.68	-578.79	-1028.9
3	1078.3	627.40	207.79	-208.84	-654.43	-1157.7
4	807.06	464.26	149.79	-162.89	-503.95	-900.41
5	845.81	487.56	158.10	-169.37	-525.31	-936.99
6	597.49	338.45	104.64	-128.65	-389.89	-704.47

16 inch base, no overlay

MC	266	285	304	323	342	361	380	399
1	825.67	572.11	340.62	120.46	-98.98	-331.43	-597.65	-915.71
2	699.45	482.34	285.93	99.95	-85.69	-284.17	-515.73	-798.05
3	786.64	531.53	315.90	111.20	-92.96	-310.04	-560.58	-862.48
4	620.79	426.45	251.89	87.61	-77.50	-254.89	-464.93	-725.03
5	644.37	443.19	262.09	91.00	-79.94	-263.64	-480.13	-746.89
6	478.20	325.34	190.36	63.95	-62.95	-202.42	-373.73	-593.71

TABLE I-2(D): 8 inch base, 3 inch overlay

MC	266	285	304	323
1	1466.0	629.89	-172.65	-998.51
2	1075.8	457.60	-130.19	-741.01
3	1232.9	566.90	-66.59	-717.41
4	887.08	402.36	-53.30	-526.53
5	903.29	469.46	69.95	-345.38
6	632.18	321.91	37.94	-255.06

8 inch base, 6 inch overlay

MC	266	285	304	323
1	1190.6	615.34	69.38	-382.55
2	911.27	467.40	50.40	-308.17
3	1003.4	561.06	146.45	-376.58
4	751.0	415.71	105.63	-296.51
5	745.18	468.70	216.88	-312.75
6	535.85	332.48	150.93	-236.52

the top of the base. The numbers below the heading MC refer to the modulus condition, all of which are depicted previously in Table 1. The numbers below the element headings are the stresses at the element centroids, in psi. A positive value denotes tension. The stresses for modulus condition one in each table are graphed in Figure 11.

Linearize Stress Distributions

As can be seen from Figure 11, the stress distributions are very nearly linear, especially in the range of Y coordinate values which encompass the crack lengths to be investigated, up to 1/2 the base thicknesses. As a result, for the purpose of applying the reverse stresses to the crack lengths, it is expedient to linearize the stress distributions by assuming a linear distribution between each element centroid. Note that element centroids are two inches apart in Figures 10 and 11. This is because each horizontal line of elements in the base is two inches thick, for all meshes. Figure 10 shows an 8 inch base. Additional elements for 12 and 16 inch bases shown in Table 4 reflect these supplemental lines of elements.

The linearized distributions are given in Table 5. Listed are the slopes, m, and the initial stress value for each interval between element centroids. Values are listed for each modulus condition. The intervals are delineated by the Y coordinate values of the appropriate element centroids. Only intervals up to 1/2 the base thickness are listed. Note that the interval between the lowest element centroids, that is between 51 and 53 inches, is extended to the bottom of the base, which is located at a Y value of 50 inches. The stress at the bottom of the base is unknown, and the same slope that acts between 51 and 53 inches is assumed to hold between 50 and 51. The stress at the bottom of the base, or the value for the initial



Figure 11. Stress Distributions for Modulus Condition 1, Parenthesis Contain Base Thickness and Surface Thickness Respectively

Table 5. Linearized Stress Distributions, psi

8 inch base, no overlay

	50-53 inches		53-55 inches	
MC	m		m	
1	579.35	2284.5	565.45	546.40
2	422.98	1672.7	410.92	383.75
3	497.05	1952.1	484.04	461.01
4	358.28	1390.6	347.29	315.74
5	376.12	1462.9	364.81	334.56
6	266.68	1018.3	258.03	218.24

12 inch base, no overlay

	50-53 inches		53-55 inches		55-57 inches	
MC	m		m		m	
1	250.75	1456.3	234.54	704.01	232.82	234.94
2	198.38	1140.8	183.44	545.64	182.23	178.77
3	225.45	1303.8	209.81	627.40	208.32	207.79
4	171.40	978.50	157.24	464.26	156.34	149.79
5	179.13	1024.9	164.23	487.56	163.74	158.10
6	129.52	727.01	116.91	338.45	116.65	104.64

16 inch base, no overlay

	50-53 inches		53-55 inches		55-57 inches		57-59 inches	
MC	m		m		m		m	
1	126.28	951.95	115.75	572.11	110.08	340.62	109.72	120.46
2	108.56	808.01	98.21	482.34	92.99	285.93	92.82	99.95
3	127.56	914.19	107.82	531.53	102.35	315.90	102.08	111.20
4	97.17	717.95	87.28	426.45	82.14	251.89	82.55	87.61
5	100.59	744.96	90.55	443.19	85.55	262.09	85.47	91.00
6	76.43	554.63	67.49	325.34	63.21	190.36	63.45	63.95

8 inch base, 3 inch overlay

	50-53 inches		53-55 inches	
MC	m		m	
1	418.06	1884.1	401.27	629.89
2	309.10	1384.9	293.90	457.60
3	333.0	1565.9	316.75	566.90
4	242.36	1129.4	227.83	402.36
5	216.92	1120.2	201.76	469.46
6	155.14	787.30	141.99	321.91

8 inch base, 6 inch overlay

	50-53 inches		53-55 inches	
MC	m		m	
1	287.63	1478.2	272.98	615.34
2	221.94	1133.2	208.50	467.40
3	221.17	1224.6	207.31	561.06
4	167.65	918.65	155.04	415.71
5	138.24	883.42	125.91	468.70
6	101.69	637.54	90.78	332.48

interval of 50-53 inches, is obtained by adding this slope to the stress at the first element centroid, located a unit distance away at 51 inches. Since there is a material (and thus stress) discontinuity between the base and the subgrade it is impossible to obtain the stress at the bottom of the base from the nearest subgrade element. It is thus necessary to assume something, and the above procedure is consistent with the concept of linearized stress distributions.

Mesh Considerations for Finite Element Runs

The sample mesh shown in Figure 12 is for a base of 8 inches, a surface of 3 inches, and a crack length of 3.5 inches (c/b of 0.4375). Also shown is an enlargement of a section of mesh in the base which is to fine to represent with the rest and an enlargement of the area immediately surrounding the crack element. This crack element and the area immediately surrounding it is common to all meshes. There is a mesh for each crack length in each base-overlay combination. The common crack element enables one to build one mesh from another quickly and easily and to be able to efficiently execute the analysis. As discussed in Chapter II, there are five crack lengths to be investigated for each base-overlay combination, and there are five base-overlay combinations targeted for analysis. Thus, there are 25 separate meshes to be considered and the efficiency afforded by a common crack element is essential.

The maximum aspect ratio in these meshes is 40:1. This occurs as far away from the crack element as possible. Near the crack, the aspect ratios are very nearly 1:1. Thus, near the crack where greater accuracy is required, the mesh is in its most accurate configuration, and far from the



Figure 12. Illustration of Mesh Around Crack

crack where accuracy is not critical, the mesh is in its least accurate configuration.

The thickness of all the meshes of this section is one inch. Therefore, all stresses applied as loads transfer as tractions of the same magnitude.

The input file corresponding to Figure 11 is listed in Appendix B.

Applying Reverse Stresses to Crack Lengths

The linearized stresses shown above are applied to the meshes created above with a reverse sign. Note that there is one mesh for each base-surface combination and one linearized stress distribution for each modulus condition of each base-surface combination. Therefore, there are 25*6 = 150 different files to be run in the finite element program. Reverse stress values calculated for the mesh shown in Figures 11 with modulus condition one are given in Table 6. These values also appear in the input file for the mesh in Figure 11 that is listed in Appendix B. Note that the values in the input file have units of force/length, not stress, but have the same magnitude as the stresses in Table 6. This is because the thicknesses of all meshes is one inch. A positive sign indicates a stress in the positive X direction.

Uncorrected K_I Values

Each of the 150 runs took between 1.50 and 3.00 minutes on a Harris 800 super mini-computer. The results are listed in Table 7. The values in the tables are uncorrected stress intensity factors in $psi\sqrt{inch}$. The negative signs indicate that the reverse stresses act to close the crack. In actuality, these stress intensity factors are positive, because the crack is

Table 6. An Example of a Reverse Stress Profile for Figure 3, MC=1.

Y COORDINATE, IN	REVERSE STRESS, PSI
50.0	1884.1
50.833	1535.7
51.5	1257.0
51.833	1117.6
52.167	978.27
52.5	838.92
52.833	699.57
53.25	525.38

Table 7. Uncorrected Stress Intensity Factors, psi/$\sqrt{in}$

8 inch base, no surface

MC	C/B 1/12	1/8	1/6	7/16	1/2
1	-916.20	-1263.99	-1490.41	-2372.08	-2387.92
2	-653.28	-891.83	-1044.41	-1585.38	-1576.26
3	-778.18	-1068.65	-1256.70	-1959.78	-1962.35
4	-543.48	-735.67	-857.06	-1257.04	-1238.55
5	-573.83	-778.89	-908.91	-1347.53	-1331.49
6	-387.04	-512.59	-589.87	-801.68	-773.87

12 inch base, no surface

MC	C/B 1/12	5/36	1/6	5/12	1/2
1	-798.13	-1147.78	-1216.62	-1490.31	-1388.27
2	-613.84	-878.07	-927.64	-1105.32	-1017.78
3	-709.19	-1017.63	-1077.19	-1304.38	-1209.25
4	-518.45	-738.42	-778.06	-906.79	-827.16
5	-545.82	-778.48	-820.98	-963.63	-881.70
6	-369.66	-520.76	-545.04	-601.43	-535.64

16 inch base, no surface

MC	C/B 1/12	1/8	1/6	7/16	1/2
1	-603.00	-779.24	-913.42	-870.49	-783.82
2	-502.45	-647.50	-757.11	-704.63	-631.38
3	-572.40	-736.91	-860.32	-800.74	-725.99
4	-439.56	-565.24	-659.70	-602.85	-537.92
5	-458.43	-589.91	-688.91	-633.19	-535.64
6	-325.38	-416.05	-483.27	-420.69	-371.11

8 inch base, 3 inch surface

MC	C/B 1/12	1/8	1/6	7/16	1/2
1	-763.07	-1165.89	-2161.30	-1962.77	-2009.58
2	-553.75	-837.89	-1540.76	-1360.62	-1382.10
3	-630.24	-957.27	-1758.64	-1593.91	-1633.61
4	-446.75	-669.68	-1218.07	-1066.60	-1082.68
5	-443.83	-664.67	-1198.61	-1083.01	-1110.89
6	-303.38	-444.61	-791.12	-682.53	-691.41

8 inch base, 6 inch surface

MC	C/B 1/12	1/8	1/6	7/16	1/2
1	-596.74	-906.85	-1655.76	-1532.27	-1579.01
2	-452.21	-681.49	-1237.18	-1122.00	-1150.22
3	-490.88	-741.00	-1338.24	-1243.83	-1284.41
4	-362.56	-541.13	-970.67	-880.61	-903.77
5	-348.11	-517.56	-915.72	-855.82	-884.99
6	-245.00	-357.48	-627.08	-567.97	-582.97

opened by the loads on the pavement. However, as mentioned previously, the magnitudes of these numbers are correct.

A sample output file is given in Appendix B. This output file corresponds to the input file in Appendix B that was discussed previously.

Stress Intensity Correction Factors

The equation used to compute the correction factors is given by equation (2) of Chapter I. In this equation, σ_e is the stress in the vicinity of the crack tip that would be applied to the portion of the crack within the crack element, if that were allowed. Because the reverse stress distribution is assumed to be linear with depth, there is no one value of reverse stress in the vicinity of the crack tip. σ_e is then defined as the average value of the reverse stress that would be applied to the length of the crack within the crack element. The average reverse stress is the stress that would be applied halfway from the crack tip to the edge of the crack element. If Y is the vertical coordinate of the crack tip, then σ_e acts at $Y = Y - z/2$. The value of z, the length of crack within the crack element, is 1/4 inches.

A negative correction factor indicates that the reverse stresses to be applied act in a manner which closes the crack. They add with the negative stress intensity factors computed in the previous section to increase the magnitude of K_I. Positive correction factors add to decrease the magnitude of the stress intensity factor.

The computed correction factors are given in Table 8. The computed stress intensity factors are added to the correction factors in order to find the final values of K_I.

Table 8. Stress Intensity Correction Factors, psi/ in

8 inch base, no surface

	C/B				
MC	1/12	1/8	1/6	7/16	1/2
1	-1572.34	-1418.26	-1264.17	-262.62	-31.492
2	-1135.84	-1023.34	-910.85	-179.63	-10.889
3	-1342.77	-1210.58	-1078.38	-219.11	-20.821
4	-954.68	-859.39	-764.10	-144.72	-1.791
5	-1004.65	-904.65	-804.62	-154.40	-4.352
6	-697.21	-626.29	-555.36	-94.34	12.052

12 inch base, no surface

	C/B				
MC	1/12	5/36	1/6	5/12	1/2
1	-986.86	-853.48	-786.79	-186.60	13.470
2	-771.70	-666.18	-613.42	-138.58	19.698
3	-882.84	-762.92	-702.96	-163.31	16.571
4	-661.04	-569.86	-524.28	-114.01	22.752
5	-692.72	-597.44	-549.08	-121.04	21.881
6	-489.65	-420.75	-386.30	-76.28	27.064

16 inch base, no surface

	C/B				
MC	1/12	1/8	1/6	7/16	1/2
1	-637.80	-570.63	-503.46	-66.84	33.914
2	-540.04	-482.29	-424.59	-49.22	37.393
3	-606.45	-538.60	-470.75	-29.73	72.049
4	-479.16	-427.47	-375.79	-39.82	37.711
5	-497.41	-443.91	-390.40	-42.61	37.649
6	-368.85	-328.19	-287.53	-23.28	37.705

8 inch base, 3 inch surface

	C/B				
MC	1/12	1/8	1/6	7/16	1/2
1	-1322.58	-1211.39	-1100.21	-382.52	-222.43
2	-971.40	-889.19	-806.98	-277.18	-159.93
3	-1105.49	-1016.92	-928.36	-357.55	-231.19
4	-796.42	-731.96	-667.50	-252.87	-161.98
5	-800.05	-742.36	-684.66	-314.21	-233.72
6	-561.14	-519.88	-478.62	-214.36	-157.72

8 inch base, 6 inch surface

	C/B				
MC	1/12	1/8	1/6	7/16	1/2
1	-1055.15	-978.65	-902.15	-409.29	-300.39
2	-808.25	-749.22	-690.20	-310.55	-227.37
3	-881.48	-822.66	-763.83	-385.63	-302.93
4	-660.52	-615.93	-571.34	-285.30	-223.45
5	-645.12	-608.36	-571.59	-336.30	-286.07
6	-464.73	-437.69	-410.64	-238.12	-201.91

The final values of K_I are given in Table 9 and illustrated in Figure 13 through Figure 17. Note that the values of K_I are positive. The actual stress intensity factors are equal in magnitude but opposite in sign to the computed ones; that is, they indicate that the crack will open under load, not close.

From the tables and graphs it can be seen that the K_I values for the 8 inch base, no surface, are greater than those of the other pavements with no surfaces. The 16 inch base has the least K_I values of the above pavements. This is intuitively reasonable. Adding a 3 inch surface to the 8 inch base generally decreases the stress intensity factors, although the K_I values for c/b = 1/6 are greater. For the 6 inch surface, the K_I values are less than their counterparts in the no surface case for all the c/b values for which stress intensity factors are calculated.

Table 9. Corrected Stress Intensity Factors

8 inch base, no surface

	C/B				
MC	1/12	1/8	1/6	7/16	1/2
1	2488.5	2682.2	2754.6	2634.7	2419.4
2	1789.1	1915.2	1955.2	1765.0	1587.1
3	2120.9	2279.2	2335.1	2178.9	1983.2
4	1498.2	1595.1	1621.2	1401.8	1240.3
5	1587.5	1683.5	1713.5	1501.9	1335.8
6	1084.2	1138.9	1145.2	896.02	761.82

12 inch base, no surface

	C/B				
MC	1/12	5/36	1/6	5/12	1/2
1	1785.0	2001.3	2003.4	1676.9	1374.8
2	1385.5	1544.2	1541.1	1243.9	998.08
3	1592.0	1780.6	1780.2	1467.7	1192.7
4	1179.5	1308.3	1302.3	1020.8	804.41
5	1238.5	1375.9	1370.8	1084.7	859.81
6	859.31	941.51	931.34	677.71	508.57

16 inch base, no surface

	C/B				
MC	1/12	1/8	1/6	7/16	1/2
1	1240.8	1349.9	1416.9	937.34	749.90
2	1042.5	1129.8	1181.7	753.85	593.99
3	1178.8	1275.5	1331.1	830.47	653.94
4	918.72	992.71	1035.5	642.67	500.21
5	955.84	1033.8	1079.3	675.80	528.11
6	694.22	744.24	770.81	443.97	333.40

8 inch base, 3 inch surface

	C/B				
MC	1/12	1/8	1/6	7/16	1/2
1	2085.7	2377.3	3261.5	2354.3	2232.0
2	1525.2	1727.1	2347.7	1637.8	1542.0
3	1735.7	1974.2	2687.0	1951.5	1864.8
4	1243.2	1401.6	1885.6	1319.5	1244.7
5	1243.9	1407.0	1883.3	1397.2	1344.6
6	864.52	964.5	1269.7	896.89	849.13

8 inch base, 6 inch surface

	C/B				
MC	1/12	1/8	1/6	7/16	1/2
1	1651.9	1885.5	2557.9	1941.6	1879.4
2	1260.5	1430.7	1927.4	1432.5	1377.6
3	1372.4	1563.7	2102.1	1629.5	1587.3
4	1023.1	1157.1	1542.0	1165.9	1127.2
5	993.24	1125.9	1487.3	1192.1	1171.1
6	709.73	795.17	1037.7	806.09	784.90



Figure 13. Distribution of Stress Intensity Factor



Figure 14. Distribution of Stress Intensity Factor



Figure 15. Stress Intensity Factor Distribution



Figure 16. Stress Intensity Factor Distribution



Figure 17. Stress Intensity Factor Distribution

CHAPTER IV: CALCULATING FRACTURE LIFE

Regression Equations for Stress Intensity Factors

In order to compute a fracture life for the pavement system the stress intensity factor distribution must be calculated for every combination of pavement and loading, and then this distribution must be used in the Paris equation. A simpler approach is to develop a series of regression equations to describe the distribution of the stress intensity factor. This eliminates the need to rerun the finite element program a large number of times to develop a series of stress intensity factors differing only slightly from each other. The equation must relate K_I to c/b.

Examining the graphs of the stress intensity factor distribution shown in the previous chapter, it is reasonable to assume a cubic distribution of K_I versus c/b, especially for the cases with no overlay. In order to define this assumed cubic relationship, regression techniques are used. A statistical package on the IBM personal computer was utilized to find the best fit coefficients to a cubic distribution. The results of the polynomial regression analysis are given in Table 10. The R^2 parameters of the regression are also listed. A value of $R^2 = 1.0$ denotes a perfect fit. Note that the fit is very good for the cases with no surface, and satisfactory for those with a surface. Plots of K_I versus c/b for both the cubic distribution and the distributions of the previous section are shown for representative cases in Figure 18 through Figure 22.

For reasons discussed previously, the range of c/b values for which stress intensity factors were computed extend from 1/12 to 1/2. For no c/b

Table 10. Regression Coefficients for Cubic Polynomial Fit to Stress Intensity Distribution.

$$K = B + B\,(C/B) + B\,(C/B) + B\,(C/B)$$

8 inch base, no surface

MC	B_0	B_1	B_2	B_3	R^2
1	2047.043	6567.108	-14172.16	5067.807	0.9861128
2	1490.105	4544.518	-10815.35	4237.885	0.9940159
3	1753.576	5513.253	-12415.28	4625.061	0.9903571
4	1260.895	3666.674	-9340.74	3857.532	0.9966238
5	1351.920	3600.485	-8792.111	3060.146	0.9971226
6	938.9210	2345.091	-6942.935	3093.236	0.9988023

12 inch base, no surface

MC	B_0	B_1	B_2	B_3	R^2
1	1297.536	7693.483	-22383.32	14619.22	0.9951294
2	1019.034	5847.388	-17613.80	11676.70	0.9962779
3	1162.857	6804.254	-20087.00	13202.72	0.9957248
4	875.8471	4887.160	-15129.88	10145.02	0.9968587
5	916.8071	5163.552	-15845.97	10587.44	0.9966850
6	654.5362	3373.223	-11169.04	7681.451	0.9978152

16 inch base, no surface

MC	B_0	B_1	B_2	B_3	R^2
1	808.9672	6928.043	-22642.82	17098.41	0.9999410
2	687.1326	5742.700	-19189.89	14661.88	0.9998762
3	776.4540	6547.792	-22345.70	17517.90	0.9998906
4	611.02611	5000.017	-16980.85	13073.25	0.9999341
5	633.80810	5223.816	-17649.63	13556.44	0.9999398
6	472.87540	3650.309	-12930.04	10141.79	0.9998798

8 inch base, 3 inch surface

MC	B_0	B_1	B_2	B_3	R^2
1	-394.5381	37465.05	-117437.1	105884.90	0.8500299
2	-235.5056	26687.00	-84582.00	76535.600	0.8609347
3	-280.6712	30515.79	-96126.81	87240.120	0.8503666
4	-137.2445	20948.11	-66598.86	60381.990	0.8641640
5	-112.6183	20547.46	-64805.32	59002.900	0.8512328
6	-12.82105	13339.98	-42658.10	38802.090	0.8696607

8 inch base, 6 inch surface

MC	B_0	B_1	B_2	B_3	R^2
1	-247.4966	28694.99	-89707.74	81544.99	0.8456994
2	-148.9915	21328.18	-67057.85	60936.81	0.8496895
3	-153.3865	23050.09	-71954.05	65549.56	0.8465933
4	-72.99951	16591.39	-52166.28	47507.98	0.8494838
5	-35.03687	15331.10	-48342.45	44153.58	0.8497349
6	17.19202	10486.71	-32985.49	30127.45	0.8487314



Figure 18. Comparison of Computed and Regression Stress Intensity Factors



Figure 19. Comparison of Computed and Regression Stress Intensity Factors



Figure 20. Stress Intensity Factor Distribution



Figure 21. Distribution of Stress Intensity Factor



Figure 22. Distribution of Stress Intensity Factors

values greater than 1/2 were stress intensity factors calculated. Thus, for c/b greater than 1/2, the assumed cubic distributions give the only K_I values; they must be relied on exclusively. The graphs of the predicted distributions for c/b greater than 1/2 are shown in Figure 23 through 27. As can be seen, the plots for all cases get smaller directly after c/b = 1/2, and then double back and increase. For the 8 inch base, no surface, the K_I values go negative and never become positive again. For the rest of the cases, K_I is always positive past c/b = 1/2, and for the 8 inch base, 3 and 6 inch surface cases K_I gets very large at c/b = 1. In addition, noting that B_0 equals K_I at c/b = 0, it can be seen that for the 8 inch base, 3 and 6 inch surface cases K_I is negative at c/b = 0. The exception is modulus condition 6 of the 6 inch surface, where K_I manages to remain positive at c/b = 0.

The predicted K_I values at c/b = 0 cannot be checked (there is no crack length on which to apply reverse stresses), but for c/b greater than 1/2 the cubic values should be checked with calculated K_I values. It may be that the cubic distributions are misleading in this range, but these values have not been checked.

Computation of Crack Propagation Histories

To calculate the rate of crack propagation, the Paris equation described in Chapter II was coded into a Fortran program to allow easy application of stress intensity factors, pavement geometry and structural properties into a program that predicted the number of load cycles to failure. Up to this point, all the necessary input has been calculated except for the initial and final crack lengths for each modulus condition, base, and surface



Figure 23. Distribution of Stress Intensity Factors Calculated by Regression Equation for Various Modulus Conditions



Figure 24. Distribution of Stress Intensity Factors Computed by Regression Equation for Various Modulus Conditions



Figure 25. Distribution of Stress Intensity Factors Computed by Regression Equation for Various Modulus Conditions



Figure 26. Distribution of Stress Intensity Factors Computed by Regression Equation for Various Modulus Conditions



Figure 27. Distribution of Stress Intensity Factors Computed by Regression Equation for Various Moduli Conditions

combination. These are found by calculating the roots of the K_I cubic distributions. The first two roots in the range $0 \leq c/b \leq 1$ which define a positive region of K_I are the endpoints, as explained in Chapter 1. If K_I is positive in the range $0 \leq c/b \leq 1$, then the endpoints are 0 and 1. The endpoints found by using this procedure are shown in Table 11. When input, if the endpoint in question is a root, then it is modified slightly so that it does not assign a zero (or negative due to round-off errors) value to K_I and thus cause computational errors. If it is a right endpoint, it is made smaller, and if it is a left endpoint it is made larger so that K_I is always positive.

The crack propagation histories for modulus condition 4, all base and surface combinations, are given in Figure 28 through Figure 32. These histories correspond to arbitrarily selected values of A and n equal to 10^{-10} and 2.0 respectively. The numbers defining these graphs can be found in the output in Appendix B, as mentioned before. The histories graphed are typical in their relationship to each other for each modulus condition and A and n combination.

It appears from the graphs that of the pavements with no surface, the 8 inch base is the most critical, followed by the 12 and then 16 inch bases. Although the number of cycles required to traverse the last crack increment in the 8 inch base is five orders of magnitude greater than the total to failure of the 12 and 16 inch bases, the load cycles needed to reach near failure in the 8 inch base is significantly smaller than the aforementioned totals. It is reasonable to believe that in such a state of near failure some perturbation could advance the crack to failure. Besides, the 8 inch base is practically destroyed at near failure anyway.

Table 11. Endpoints For Crack Propagation Histories

8 inch base, no surface

MC	LEFT	RIGHT
1	0.0	0.925978
2	0.0	0.880403
3	0.0	0.905504
4	0.0	0.849452
5	0.0	0.837094
6	0.0	0.784196

12 inch base, no surface

MC	LEFT	RIGHT
1	0.0	1.0
2	0.0	1.0
3	0.0	1.0
4	0.0	1.0
5	0.0	1.0
6	0.0	1.0

16 inch base, no surface

MC	LEFT	RIGHT
1	0.0	1.0
2	0.0	1.0
3	0.0	1.0
4	0.0	1.0
5	0.0	1.0
6	0.0	1.0

8 inch base, 3 inch surface

MC	LEFT	RIGHT
1	0.010900	1.0
2	0.009084	1.0
3	0.009478	1.0
4	0.006693	1.0
5	0.005579	1.0
6	0.000964	1.0

8 inch base, 6 inch surface

MC	LEFT	RIGHT
1	0.008869	1.0
2	0.007145	1.0
3	0.006798	1.0
4	0.004462	1.0
5	0.002302	1.0
6	0.0	1.0



Figure 28. Progression of Crack (c) Through Base (b) as a Function of Load Cycles, N



Figure 29. Progression of Crack (c) Through Base (b) as a Function of Load Cycles, N



Figure 30. Progression of Crack (c) Through Base (b) as a Function of Load Cycles, N



Figure 31. Progression of Crack (c) Through Base (b) as a Function of Load Cycles, N



Figure 32. Progression of Crack (c) Through Base (b) as a Function of Load Cycles, N

The 3 and 6 inch surfaces are added to the 8 inch base with the intent of increasing the fatigue life. From the graphs it is seen that theoretically they do, but perhaps realistically they won't. In both the 3 and 6 inch surface cases, it takes a tremendous amount of load cycles to advance the crack through the first increment of approximately 0.05 inches. After that, though, it takes less cycles to propagate the crack to failure than it does for the crack to reach near failure in the no surface case. Therefore, if the crack were somehow jumped past the initial increment in the 3 and 6 inch surface cases, due to say a starter flaw, which may typically have dimensions capable of doing this, those pavements would be more critical than the no surface case. It is certainly reasonable to think that the first increment could be jumped, as it is assumed that a zone of negative K_I is jumped to get to the first increment in the first place. In this case the negative zone is only about 0.01 inches at most, so that it is no great achievement to bypass it. So, in one sense, adding a surface will greatly postpone failure as long as the negative K_I zone and the first crack increment are not vaulted. In another sense, if the above were circumvented, adding a surface could hasten failure.

As would be expected, the 3 inch surface case requires more cycles to failure than the 6 inch surface case for the same pavement structure.

Calculations With Actual Laboratory Fracture Properties

Extensive laboratory studies conducted at Texas A&M University have indicated that the fracture parameters, A and n can be predicted from tests along with K_{Ic} for stabilized materials. These parameters are necessary to predict the fracture life of a material insitu. Typical values determined are as follows:

CEMENT LEVEL		E=355,600 psi v = 0.15
10 %	CREEP VALUES	$A=8.12\times10^{-59}$
$K_{IC}=138.6$		n=25.28
	FATIGUE VALUES	$A=15.4\times10^{-27}$
		n=10.0
		E=597,600 psi v = 0.15
15 %	CREEP VALUES	$A=1.45\times10^{-53}$
$K_{IC}=209.3$		n=21.24
	FATIGUE VALUES	$A=10\times10^{-51}$
		n=22.0

Comparison of these critical stress intensity factors indicates that the stress intensity factors calculated using the procedures outlined here are all larger than the critical stress intensity factors which means that fracture will proceed instantaneously. This indicates the inaccuracy of the pavement structure selected for modelling the stress intensity factors calculated.

CHAPTER V: CONCLUSIONS AND RECOMMENDATIONS

The analysis procedure presented in this report illustrates the complexities involved in calculating stress intensity factors, and applying them to a structure to predict cycles to failure. The stress intensity factors used in this analysis are not as accurate as may be desired, due to the use of plane strain, plane stress solutions used in the finite element procedure to calculate the initial stresses. The modification of more sophisticated programs to accept the fracture elements in an axi-symmetric analysis would increase the accuracy of the predictions of fracture in the cement stabilized base materials, or any material susceptible to fracture.

The methodology of applying the principles of fracture, as demonstrated in the development of this report are applicable to a design methodology, and indicate the modularized approach which must be taken to adequately characterize the pavements, their geometry, and the loading conditions which may be expected to occur in an actual airfield pavement.

The principles of fracture mechanics and crack propagation can be applied to pavement design life, to account for the gradual failure due to repeated loading over fracture susceptible materials. The parameters required to predict crack propagation are the material properties of A and n, as described in this report. A significant amount of testing has gone into evaluating these parameters for cement stabilized materials, and the influence of these material properties on fracture life was shown.

The predicted stress intensity factors were high, due directly to the level of structure modeled and the magnitude of loading investigated.

A broader range of loading conditions, and a thicker pavement structure would have produced more moderate stress intensity factors which would have shown a more pronounced effect on fracture life than was seen in this report.

1. The methodology developed in this study indicates the potential for considering fracture in pavement design methodology.
2. The stress calculation scheme can be refined and replaced by a general program to analyze an axisymmetric problem with multiple wheel loadings. This can be a simple elastic layer program, a stress dependent elastic layer program, or even a sophisticated stress dependent finite element program such as Illi- Pave.
3. The hybrid crack tip element provides a simple means of accurately evaluating the influence of loading on fracture life in fracture susceptible layers of a pavement system given the stresses present in the layers.
4. The modular approach developed to provide stress intensity factors using regression techniques to replace repetitive calculations with the finite element program is an accurate procedure to obtain the stress intensity factors in a manner applicable to design without extensive use of computer execution time.

REFERENCES

1. Chang, Hang-Sun, "Prediction of Thermal Cracking in West Texas," Masters Thesis, Texas A&M University, Department of Civil Engineering (1975).

2. Desai, C. S., and Abel, J. F., Introduction to the Finite Element Method, Van Nostrand Reinhold Company, 1972.

3. Pian, T.H.H., Tong, P., Luk, C. H., "Elastic Crack Analysis by a Finite Element Hybrid Method," (paper) 3rd Conf. Matrix Meth. Struct: Mech., Wright-Patterson AFB, Ohio (1971).

4. Pian, T.H.H., Tong, P., Lasry, S. J., "A Hybrid Element Approach to Crack Problems in Plane Elasticity," IJNME, Vol. 7, 1973, pp. 297-308.

5. Tong, P., Lin, K. Y., Orringer, O., "Effect of Shape and Size on Hybrid Crack-Containing Finite Elements," Computational Fracture Mechanics, ASME, 1975.

APPENDIX A: NOTATION AND CONVERSION FACTORS

SYMBOL	MEANINGS
A	regression constant in fracture equation; area in other cases
A_m	Element areas in finite element development
b	base course thickness in fracture analysis
c	crack length within a pavement layer
C_K	stress intensity correction factor
$C_{i,j,k,l}$	Elastic Compliance Tensor
e	2.71828
E	Young's modulus of elasticity
G	shear modulus
K	stress intensity factor
m	creep exponent
n	regression constant (exponent) in fracture equation
N	number of cycles in fracture
P	load
q	nodal displacements
R	statistical correlation coefficient
r	radius
S	Surface for integration
T	Traction vector normal to integration path
u	boundary displacement
x,y	x_1, y_1 directions respectively
ϵ	error in stress intensity predictions, strain
ζ	local coordinate axis
θ	angle
ν	Poisson's ratio
σ	stress
σ_3	principal stress
τ	shear stress
Σ	summation
$\sqrt{}$	square root
ln	natural (Naperian) logarithm (base e)
$\mathcal{G}$	Strain energy release rate
ξ	coordinate distance from crack tip
σ_e	stress applied to crack tip

APPENDIX B: DESCRIPTION OF PROGRAM UNITS

Finite Element Fracture Program

A flow diagram of subroutines is shown in Figure B-1. The following is a brief description of each subroutine and the input data format follows.

DATAIN:

Reads and echo prints all data pertaining to the conventional elements. It also performs checks on this data.

ASEMBL;

Initializes and assembles the glabal stiffness matrix (including the crack element) and the global load vector. Modifies the above to reflect the geometric boundary conditions.

QUAD:

Computes the stress-strain matrix, stiffness matrix, body force vector, and strain-displacement matrix of either a 4-CST quadrilateral or a triangular element.

CST:

Computes the strain-displacement matrix, stiffness matrix, and body force vector of a CST element.

GEOMBC:

Applies prescribed displacement boundary conditions at a single, specified node.



Figure B-1. Flow Diagram of Program for Finite Element Fracture Calculations

CRACK:

Reads the input data pertaining to the crack element. Computes the constants and of Section II. Incorporates the crack element stiffness matrix into the global stiffness matrix which had previously contained stiffnesses from only conventional elements.

HYBRID:

Computes the matrices [G] and [H] of Section II. Computes the crack element stiffness matrix. Computes the $(B_I)^T$ and $(B_{II})^T$ row vectors of Section II.

LOC:

The crack element stiffness matrix is not derived in two-dimensional array form but rather in vector form. Thus, in CRACK and SIFAC where this stiffness matrix is used in calculations and manipulations, some operator must be used to translate from two- to one-dimensional form. This operator is LOC. This is probably done to save memory.

MFSD:

Uses numerical methods to perform the integration implied by equations (16) and (17) of Section II.

SINV:

Performs the inversion of [H].

BANSOL:

Triangularizes the global banded stiffness matrix by symmetric Gauss-Doolittle decomposition and/or solves for the global displacement vector corresponding to a given load vector

STRESS:

Computes strains, stresses, and principal stresses for conventional elements. Computes the strain energy due to all the conventional elements which can be used to calculate stress intensity factors by energy methods, as mentioned in Section I. Prints stresses and principal stresses at element centroids, and the strain energy.

SIFAC:

Computes the stress intensity factors by equations (23) in Section II. Computes the crack element strain energy and the global strain energy, which can be used to compute stress intensity factors by energy methods, as in Section I. Prints the crack element strain energy.

Input Guide- Descriptions are included for each card.

IDENTIFICATION CARD:

One card per problem: Format (I5,3x,9A8)

cc 1-5 NPROB: The problem number. If NPROB = 0, execution of the program is halted.

cc 9-80 TITLE(I): Title of the problem. The vector has 9 elements, each of which contains 9 characters of the title.

Multiple problems can be handled, but as soon as the next problem is read the previous problem is lost, so a problem cannot be recalled.

BASIC PARAMETERS:

One card per problem: Format 615

cc 1-5 NNP: Number of nodal points

cc 6-10 NEL: Number of conventional elements

cc 11-15 NMAT: Number of different materials

cc 16-20 NLSC: Number of surface tractions

cc 21-25 NOPT: Option for stress state. 1 = plane strain, 2 = plane stress.

cc 26-30 NBODY: Option for body force. 0 = no weight, 1 = weight in the negative y direction.

cc 31-35 NCKEL: Number of crack elements.

MATERIAL PROPERTIES

NMAT cards per problem: Format 4F10.0

cc 1-10 E: Modulus of elasticity

cc 11-20 PR: Poisson's ratio

cc 21-30 RO: Density of the material

cc 31-40 TH: Thickness of the material

NODAL POINT DATA:

Up to NNP cards per problem: Format (215,4F10.0)

cc 1-5 M: Nodal point number

cc 6-10 KODE(I): Index of displacement and concentrated load conditions at note I. The values Kode can assume and the conditions assigned to each are given in Table IV-1.

cc 11-20 X: Horizontal coordinate of node I.

cc 31-30 Y: Vertical coordinate of node I.

cc 31-40 ULX: Concentrated load or displacement in X direction at node I.

cc 41-50 ULY: Concentrated load or displacement in Y direction at node I.

Usually one card is needed for each node. However, if some nodes fall on a straight line and are equidistant, data for only the first and last points of this group are needed. Intermediate nodal point data are automatically generated by linear interpolation. The nodal data must be entered in order from smallest to largest, leaving out those nodes which are to be interpolated. The nodes which are interpolated are assigned values of KODE = 0, ULX = 0, and ULY = 0. The signs of presecribed nodal displacements or forces follow the signs of the coordinate directions assigned by the user.

ELEMENT DATA:

Up to NEL cards per problem: Format 615.

cc 1-5 M: The element number

cc 6-10 IE(M,1): The index of the first node of a CST or 4-CST quadrilateral element.

cc 11-15 IE(M,2): The index of the second node of a CST or 4-CST quadrilateral element.

cc 16-20 IE(M,3): The index of the third node in a CST or 4-CST quadrilateral element.

cc 21-25 IE(M,4): The index of the fourth node in a CST or 4-CST quadrilateral element. If it is a CST element, the index of fourth node equals that of the third node; that is, IE(M,3) = IE(M,4).

cc 26-30 IE(M,5): Material type number corresponding to element M.

Usually, one card is needed for each element. However, if some elements are on a line in such a way that their corner node indexes each increase by one compared to the previous element, only the data for the first element on the line need be input. As the elements on the line are generated by adding one to each node of the preceeding element, starting with the first element on the line, the last element on a line needn't be input. However, data for the last element in the assemblage must be input whether it could be generated or not. Also, please note that triangular elements cannot be generated from quadrilateral elements because the third and fourth indexes of a triangular element are equal. The same material type as the first element on a line is assigned to all elements generated on that line.

For a right-handed coordinate system, the nodal indices for an element must be input counter-clockwise around the element.

SURFACE TRACTIONS:

As many cards as needed: Format (215,4F10.0)

cc 1-5	ISC:	I, the first node upon which tractions act.
cc 6-10	JSC:	J, the second node upon which tractions act.
cc 11-20	SURX1:	The intensity of the traction in the X direction acting at node I.
cc 21-30	SURX2:	The intensity of the traction in the X direction acting at node J.
cc 31-40	SURY1:	The intensity of the traction in the Y direction acting at node I.
cc 41-50	SURY2:	The intensity of the traction in the Y direction acting at node J.

Surface tractions must be specified between two adjacent nodes only. The tractions in both the X and Y directions are assumed to vary linearly between the two nodes. Intensities are expressed in units of force/length so that pressures must be multiplied by the thickness before being input into the computer. The signs of the tractions follow the directions of the coordinate axes assigned by the user.

CRACK ELEMENT DATA:

There are NCKEL cards per problem for each of the two types of card which comprise the crack element data.

Card one: Format (215,2F10.0,15)

cc 1-5 KEY: The type of crack element. 1 = five node case, 2 = nine node case.

cc 6-10 MATYP: The type of material where the crack element is placed.

cc 11-20 XC: The horizontal coordinate of the crack tip.

cc 21-30 YC: The vertical coordinate of the crack tip.

cc 31-35 NCOT: Flag which determines which direction nodal indexes are to be counted around the crack element. For the five node case 1 = clockwise, 0 = counter-clockwise.

Card two: Format 1015

cc (5I-4)-5I KCRK(I): Nodal incidence for the Ith node of the crack element.

cc (5K+1)-5(K+1) MAXDIF: Maximum difference between the nodal incidences of the crack element. Used to compute the bandwidth after the addition of the crack element.

For the five node case there are five incidences input for the crack element (K = 5) and for the nine node case there are nine (K = 9). In either case the input for MAXDIF immediately follows the last incidence input. All crack element data is omitted if NCKEL = 0.

The listing of the finite element computer code is given on the following pages.

```
C      PROGRAM FEQLD(INPUT,OUTPUT,TAPE5=INPUT,TAPE6=OUTPUT,
C     +TEMP1,TEMP2,TEMP3,TEMP4,TEMP8,
C     +TAPE1=TEMP1,TAPE2=TEMP2,TAPE3=TEMP3,TAPE4=TEMP4,TAPE8=TEMP8)
C        IMPLICIT REAL*8(A-H,O-Z)
       PROGRAM FEQLD
       IMPLICIT REAL(A-H,O-Z)
       DIMENSION TITLE(9)
       COMMONE(10),PR(10),RO(10),TH(10),X(700),Y(700)
       COMMON/CONS/NNP,NEL,NMAT,NSLC,NOPT,NBODY,MTYP,NCKEL
       COMMON/ONE/QK(10,10),Q(10),B(3,10),C(3,3),BT(3,6),XQ(5),YQ(5)
       COMMON/TWO/IBAND,NEQ,R(1400),AK(1400,100)
       COMMON/T1/IE(700,5)
       DATA MAXEL,MAXNP,MAXMAT,MAXBW/700,700,10,100/
C
C PROBLEM  IDENTIFICATION  AND  DESCRIPTION
C
 9999 READ(15,100)NPROB,(TITLE(I),I=1,9)
      IF(NPROB.LE.0)GOTO999
 1020 WRITE(16,200)NPROB,(TITLE(I),I=1,9)
      CALL DATAIN(MAXEL,MAXNP,MAXMAT,MAXSLC,ISTOP)
      MAXDOF=2*MAXNP
C
C COMPUTE  MAX, NODAL DIFFERENCE AND SEMI-BANDWIDTH, EQ. (6-1)
      MAXDIF=0
      DO 1I=1,NEL
      DO 1J=1,4
      DO 1K=1,4
      LL=IABS(IE(I,J)-IE(I,K))
      IF(LL.GT.MAXDIF)MAXDIF=LL
    1 CONTINUE
      IBAND=2*(MAXDIF+1)
      NEQ=2*NNP
      IF(IBAND.GT.MAXBW)GOTO900
      IF(ISTOP.GT.0)GOTO999
      CALL ASEMBL(ISTOP)
      IF(ISTOP.GT.0)GOTO999
C
C  TRIANGULARIZE STIFFNESS MATRIX, EQ, (2-2), KKK=1
C
C  SOLVE FOR DISPLACEMENTS CORRESP, TO LOAD VECTOR R, EQ,(2-3), KKK=2
      CALL BANSOL(AK,R,NEQ,IBAND,MAXDOF,MAXBW)
      WRITE(16,300)(I,R(2*I-1),R(2*I),I=1,NNP)
C
      CALL STRESS(WORK)
      WRITE(16,605)
  605 FORMAT("1")
      TOTAL=0.0
      SUM=0.0
      IF(NCKEL.EQ.0)GOTO645
      REWIND 12
      WRITE(16,37)NCKEL
   37 FORMAT("0",5X,"NCKEL=",I3)
      DO 36I=1,NCKEL
      CALL SIFAC(I,TOTAL)
      SUM=SUM+TOTAL
   36 CONTINUE
  645 CONTINUE
      ENERGY=SUM+WORK
      WRITE(16,400)ENERGY
  400 FORMAT("_",5X,"...TOTAL STRAIN ENERGY =",G20.8,". . . ")
      GOTO 9999
  900 WRITE(16,901)IBAND,MAXBW
      GOTO 9999
  100 FORMAT(I5,3X,9A8)
  200 FORMAT(/"1PROBLEM",I5,".. ",9A8/)
  300 FORMAT("1OUTPUT TABLE 1.. NODAL DISPLACEMENTS"//13X,"NODE",9X,
     +"U = X-DISP.",9X,"V = Y-DISP."/(5X,I12,2E20.8))
  901 FORMAT(///" BANDWIDTH =",I4," EXCEEDS MAX, ALLOWABLE =",I4//
     +" GO ON TO NEXT PROBLEM          ")
  999 STOP
      END
      SUBROUTINE DATAIN(MAXEL,MAXNP,MAXMAT,MAXSLC,ISTOP)
C       IMPLICIT REAL*8(A-H,O-Z)
      IMPLICIT REAL(A-H,O-Z)
      COMMON/CONS/NNP,NEL,NMAT,NSLC,NOPT,NBODY,MTYP,NCKEL
      COMMONE(10),PR(10),RO(10),TH(10),X(700),Y(700)
      COMMON/T1/IE(700,5)
C
      ISTOP=0
      REWIND 14
      REWIND 18
      READ(15,1)NNP,NEL,NMAT,NSLC,NOPT,NBODY,NCKEL
C
      WRITE(16,100)NNP,NEL,NMAT,NSLC,NOPT,NBODY
C
      WRITE(16,200)NCKEL
C CHECKS TO BE SURE INPUT DATA DOES NOT EXCEED STORAGE CAPACITY
      IF(NNP.LE.MAXNP)GOTO201
      ISTOP=ISTOP+1
      WRITE(16,251)MAXNP
  201 IF(NEL.LE.MAXEL)GOTO202
      ISTOP=ISTOP+1
      WRITE(16,252)MAXEL
  202 IF(NMAT.LE.MAXMAT)GOTO204
      ISTOP=ISTOP+1
      WRITE(16,253)MAXMAT
  204 IF(ISTOP.EQ.0)GOTO205
      WRITE(16,255)ISTOP
      STOP
C
  205 READ(15,2)(E(I),PR(I),RO(I),TH(I),I=1,NMAT)
      WRITE(16,101)
C  READ AND PRINT NODAL DATA (REF. 1)
      WRITE(16,51)(I,E(I),PR(I),RO(I),TH(I),I=1,NMAT)
      WRITE(16,103)
      N=1
    5 READ(15,3)M,KODE,X(M),Y(M),ULX,VLY
      UULX=ULX
      VVLY=VLY
      KKODE=KODE
      IF(M-N)4,442,7
    4 WRITE(16,105)M
      WRITE(16,52)M,KODE,X(M),Y(M),ULX,VLY
      ISTOP=ISTOP+1
      GOTO 5
    7 DF=M+1-N
      RX=(X(M)-X(N-1))/DF
      RY=(Y(M)-Y(N-1))/DF
    8 KODE=0
      X(N)=X(N-1)+RX
```

AD-A167 106 FRACTURE IN STABILIZED SOILS VOLUME 2(U) TEXAS 2/2
TRANSPORTATION INST COLLEGE STATION D N LITTLE ET AL.
31 DEC 85 AFOSR-TR-86-0242-VOL-2 F49620-82-K-0027
UNCLASSIFIED F/G 8/13 NL





MICROCOPY CHART

```
      Y(N)=Y(N-1)+RY
      ULX=0.0
      VLY=0.0
      GOTO 6
  442 ULX=UULX
      VLY=VVLY
      KODE=KKODE
    6 WRITE(16,52)N,KODE,X(N),Y(N),ULX,VLY
      WRITE(14)N,KODE,ULX,VLY
      N=N+1
      IF(M-N)9,442,8
    9 IF(N.LE.NNP)GOTO5
C
C  READ AND PRINT ELEMENT PROPERTIES, TABLE 6-4
      WRITE(16,106)
   13 L=0
   14 READ(15,15)M,(IE(M,I),I=1,5)
   16 L=L+1
      IF(M-L)117,17,18
  117 WRITE(16,118)M
      WRITE(16,53)M,(IE(M,I),I=1,5)
      ISTOP=ISTOP+1
      GOTO 14
   18 IE(L,1)=IE(L-1,1)+1
      IE(L,2)=IE(L-1,2)+1
      IE(L,3)=IE(L-1,3)+1
      IE(L,4)=IE(L-1,4)+1
      IE(L,5)=IE(L-1,5)
   17 WRITE(16,53)L,(IE(L,I),I=1,5)
      IF(M-L)20,20,16
   20 IF(NEL-L)21,21,14
   21 CONTINUE
C
C READ AND PRINT SURFACE LOADING(TRACTION) CARDS
      IF(NSLC.EQ.0)GOTO31
   30 WRITE(16,108)
      DO 40L=1,NSLC
      READ(15,41)ISC,JSC,SURX1,SURX2,SURY1,SURY2
      WRITE(16)ISC,JSC,SURX1,SURX2,SURY1,SURY2
   40 WRITE(16,42)ISC,JSC,SURX1,SURX2,SURY1,SURY2
   31 IF(ISTOP.EQ.0)GOTO999
      WRITE(16,900)ISTOP
C
    1 FORMAT(7I5)
  100 FORMAT("0INPUT TABLE 1.. BASIC PARAMETERS  "//5X,
     +" NUMBER OF NODAL POINTS. . . . . .",I5/5X,
     +" NUMBER OF ELEMENTS. . . . . .",I5/5X,
     +" NUMBER OF DIFFERENT MATERIALS . . . . .",I5/5X,
     +" NUMBER OF SURFACE LOAD CARDS. . . . . .",I5/5X,
     +" 1 = PLANE STRAIN, 2 = PLANE STRESS. . .",I5/5X,
     +" BODY FORCES(1 = IN -Y DIREC., 0 = NONE)",I5)
  200 FORMAT("0",6X,"NUMBER OF CRACK ELEMENTS. . .",I5)
  251 FORMAT(////" TOO MANY NODAL POINTS, MAXIMUM =",I5)
  252 FORMAT(////" TOO MANY ELEMENTS, MAXIMUM = ",I5)
  253 FORMAT(////" TOO MANY MATERIALS, MAXIMUM =",I5)
  255 FORMAT(////" EXECUTION HALTED BECAUSE OF",I5," FATAL ERRORS"/)
    2 FORMAT(4F10.0)
  101 FORMAT("0INPUT TABLE 2.. MATERIAL PROPERTIES"//"  MATERIAL",5X,
     +"MODULUS OF",6X,"POISSON'S",7X,"MATERIAL",7X,"MATERIAL"/4X,
     +"NUMBER",5X,"ELASTICITY",6X,"  RATIO",8X,"DENSITY",6X,
     +"THICKNESS")
   51 FORMAT(I10,4E15.4)
  103 FORMAT("1INPUT TABLE 3.. NODAL POINT DATA "//5X,"NODAL",48X,
     +"X-DISP.",8X,"Y-DISP."/5X,"POINT",6X,"TYPE",14X,"X",14X,"Y",8X,
     +"OR LOAD",8X,"OR LOAD")
    3  FORMAT(2I5,4F10.0)
  105 FORMAT(5X,"ERROR IN CARD NO.",I5/)
   52 FORMAT(2I10,4E15.4)
  106 FORMAT("1INPUT TABLE 4.. ELEMENT DATA      "//11X,
     +"GLOBAL INDICES OF ELEMENT NODES"/3X,"ELEMENT",7X,"1",7X,"2",7X,
     +"3",7X,"4",2X,"MATERIAL")
  118 FORMAT(5X,"ERROR IN ELEMENT CARD NO.",I5/)
   15 FORMAT(6I5)
   53 FORMAT(I10,4I8,I10)
  108 FORMAT("1INPUT TABLE 5.. SURFACE LOADING DATA"//17X,
     +"SURFACE LOAD INTENSITIES AT NODES"/4X,"NODE I",4X,"NODE J",10X,
     +"XI",10X,"XJ",10X,"YI",10X,"YJ")
   41 FORMAT(2I5,4F10.0)
   42 FORMAT(2I10,4E12.4)
  900 FORMAT(///" ASSEMBLY AND SOLUTION WILL NOT BE PERFORMED,",I5,
     +"  FATAL CARD ERRORS  ")
  999 RETURN
      END
      SUBROUTINE ASEMBL(ISTOP)
C       IMPLICIT REAL*8(A-H,O-Z)
      IMPLICIT REAL(A-H,O-Z)
      DIMENSION LP(8)
C
      COMMON/CONS/NNP,NEL,NMAT,NSLC,NOPT,NBODY,MTYP,NCKEL
      COMMON/ONE/PR(10),RO(10),TH(10),X(700),Y(700)
      COMMON/ONE/QK(10,10),Q(10),B(3,10),C(3,3),BT(3,6),XQ(5),YQ(5)
      COMMON/TWO/IBAND,NEQ,R(1400),AK(1400,100)
      COMMON/T1/IE(700,5)
      REWIND 11
      REWIND 12
      REWIND 13
      REWIND 14
      REWIND 18
C  INITIALIZE
      ISTOP=0
C  INITIALIZE PARTS OF MATRICES C AND BT
      BT(1,4)=0.0
      BT(1,5)=0.0
      BT(1,6)=0.0
      BT(2,1)=0.0
      BT(2,2)=0.0
      BT(2,3)=0.0
      C(1,3)=0.0
      C(2,3)=0.0
      C(3,1)=0.0
      C(3,2)=0.0
C
C INITIALIZE OVERALL STIFFNESS MATRIX AK AND OVERALL LOAD VECTOR R
      DO 2I=1,NEQ
      R(I)=0.0
      DO 2J=1,IBAND
    2 AK(I,J)=0.0
C
C COMPUTE  ELEMENT  STIFFNESSES AND LOADS ONE BY ONE
C
```

```
      DO 10M=1,NEL
      IF(IE(M,5).GT.0)GOTO11
      ISTOP=ISTOP+1
      GOTO 10
   11 CALL QUAD(M,AREA)
      IF(AREA.GT.0.0)GOTO16
      ISTOP=ISTOP+1
      WRITE(16,20)M
C
C
C STORE ELEMENT STIFFNESS MATRIX TO COMPUTE STORED ENERGY
   16 IF(IE(M,3).EQ.IE(M,4))GOTO201
      LIM=10
      GOTO 205
  201 LIM=8
  205 WRITE(13)LIM,((QK(I,J),J=1,LIM),I=1,LIM)
C
C  CONDENSE ELEMENT STIFF, FROM 10X10 TO 8X8, EQ.(5-64), AND ELEMENT
C  LOADS FROM 10X1 TO 8X1, EQ.(5-64D).    (REF.2)
      IF(IE(M,3).EQ.IE(M,4))GOTO26
      DO 31J=1,2
      IJ=10-J
      IK=IJ+1
      PIVOT=QK(IK,IK)
      DO 32K=1,IJ
      F=QK(IK,K)/PIVOT
      QK(IK,K)=F
      DO 331=K,IJ
      QK(I,K)=QK(I,K)-F*QK(I,IK)
   33 QK(K,I)=QK(I,K)
   32 Q(K)=Q(K)-QK(IK,K)*Q(IK)
   31 Q(IK)=Q(IK)/PIVOT
C
C STORE MULTIPLIERS,PIVOTS,CONDENSED LOADS, STRAIN-DISP, AND STRESS-STR
C MATRICES ON SCRATCH TAPE NO. 1 (TO BE USED LATER TO COMPUTE STRAINS A
C STRESSES )
   26 WRITE(11)((QK(I,J),J=1,10),I=9,10),Q(9),Q(10),((B(I,J),J=1,10),I=
     +1,3),((C(I,J),J=1,3),I=1,3),XQ(5),YQ(5)
C
C  ASSEMBLE STIFF.  AND  LOADS , DIRECT STIFF, METHOD, SEC, 6-5.
C
      LIM=8
      IF(IE(M,3).EQ.IE(M,4))LIM=6
      DO 401=2,LIM,2
      IJ=I/2
      LP(I-1)=2*IE(M,IJ)-1
   40 LP(I)=2*IE(M,IJ)
      DO 50LL=1,LIM
      I=LP(LL)
      R(I)=R(I)+Q(LL)
      DO 50MM=1,LIM
      J=LP(MM)-I+1
      IF(J.LE.0)GOTO50
      AK(I,J)=AK(I,J)+QK(LL,MM)
   50 CONTINUE
   10 CONTINUE
      IF(NCKEL.EQ.0)GOTO35
      DO 141=1,NCKEL
   14 CALL CRACK
   35 CONTINUE
C
C ADD EXTERNALLY APPL, CONC, NODAL LOADS TO R
      DO 55N=1,NNP
      READ(14)M,KODE,ULX,VLY
      IF(KODE.EQ.3)GOTO55
      K=2*N
      IF(KODE.EQ.1)GOTO57
      R(K-1)=R(K-1)+ULX
      IF(KODE.NE.0)GOTO55
   57 R(K)=R(K)+VLY
   55 CONTINUE
C
C  CONVERT LINEARLY VARYING SURFACE TRACTIONS TO STATIC EQUIVALENTS,
C  AND ADD TO OVERALL LOAD VECTOR  R, EQ,(5-61A).
      IF(NSLC.EQ.0)GOTO60
      DO 61L=1,NSLC
      READ(18)ISC,JSC,SURX1,SURX2,SURY1,SURY2
      I=ISC
      J=JSC
      II=2*I
      JJ=2*J
      DX=X(J)-X(I)
      DY=Y(J)-Y(I)
      EL=SQRT(DX*DX+DY**2)
      PXI=SURX1*EL
      PXJ=SURX2*EL
      PYI=SURY1*EL
      PYJ=SURY2*EL
      R(JJ-1)=R(II-1)+PXI/3.0+PXJ/6.0
      R(JJ-1)=R(JJ-1)+PXI/6.0+PXJ/3.0
      R(II)=R(II)+PYI/3.0+PYJ/6.0
      R(JJ)=R(JJ)+PYI/6.0+PYJ/3.0
   61 CONTINUE
C
C INTRODUCE KINEMATIC CONSTRAINTS (GEOMETRIC BOUNDARY CONDITIONS),
C  EQ,(6-16),          REF, 1.
C
   60 CONTINUE
      REWIND 14
      DO 70M=1,NNP
      READ(14)N,KODE,ULX,VLY                                          ASE
      IF(KODE.GE.0.AND.KODE.LE.3)GOTO72
      ISTOP=ISTOP+1
      GOTO 70
   72 IF(KODE.EQ.0)GOTO70
      IF(KODE.EQ.2)GOTO71
      CALL GEOMBC(ULX,2*M-1)
      IF(KODE.EQ.1)GOTO70
   71 CALL GEOMBC(VLY,2*M)
   70 CONTINUE
      ENDFILE11
      ENDFILE12
      ENDFILE13
      ENDFILE14
      ENDFILE16
      IF(ISTOP.EQ.0)GOTO81
      WRITE(16,100)ISTOP
   20 FORMAT(/5X," AREA OF ELEMENT ",I5,"  IS NEGATIVE "/)
  100 FORMAT(////" SOLUTION WILL NOT BE PERFORMED BECAUSE OF",I5,
     +"   DATA ERRORS "/)
```

```
      81 RETURN
         END
         SUBROUTINE QUAD(M,TOTALA)
C           IMPLICIT REAL*8(A-H,O-Z)
         IMPLICIT REAL(A-H,O-Z)
         COMMON/CONS/NNP,NEL,NMAT,NSLC,NOPT,NBODY,MTYP,NCKEL
         COMMONE(10),PR(10),RO(10),TH(10),X(700),Y(700)
         COMMON/ONE/QK(10,10),Q(10),B(3,10),C(3,3),BT(3,6),XQ(5),YQ(5)
         COMMON/TWO/IBAND,NEQ,R(1400),AK(1400,100)
         COMMON/T1/IE(700,5)
C
         I=IE(M,1)
         J=IE(M,2)
         K=IE(M,3)
         L=IE(M,4)
         MTYP=IE(M,5)
         TOTALA=0.0
C
C  CONSTRUCT STRESS-STRAIN MATRIX C,EQ.(3-16C).  FOR PLANE STRAIN
C  NOPT=1, AND FOR PLANE STRESS  NOPT=2,  PRESENT  CODE  IS FOR
C  ISOTROPIC MATERIALS
         IF(NMAT.EQ.1.AND.M.GT.1)GOTO5
         IF(NOPT.EQ.2)GOTO2
         CF=E(MTYP)/((1.0+PR(MTYP))*(1.0-2.0*PR(MTYP)))
         C(1,1)=CF*(1.0-PR(MTYP))
         C(1,2)=CF*PR(MTYP)
         C(2,1)=C(1,2)
         C(2,2)=C(1,1)
         C(3,3)=CF*(1.0-2.0*PR(MTYP))/2.0
         GOTO 5
       2 CF=E(MTYP)/(1.0-PR(MTYP)*PR(MTYP))
         C(1,1)=CF
         C(1,2)=PR(MTYP)*CF
         C(2,1)=C(1,2)
         C(2,2)=CF
         C(3,3)=CF*(1.0-PR(MTYP))/2.0
       5 LIM=4
         IF(K.EQ.L)LIM=3
         XQ(5)=0.0
         YQ(5)=0.0
         DO 10N=1,LIM
         NN=IE(M,N)
         XQ(N)=X(NN)
         YQ(N)=Y(NN)
         XQ(5)=XQ(5)+X(NN)/FLOAT(LIM)
      10 YQ(5)=YQ(5)+Y(NN)/FLOAT(LIM)
C
C  INITIALIZE QUAD. STIFFNESS,LOAD VECTOR AND STRAIN-DISPLACEMENT VECTOR
         DO 13II=1,10
         Q(II)=0.0
         DO 12JJ=1,10
      12 QK(II,JJ)=0.0
         DO 13JJ=1,3
      13 B(JJ,II)=0.0
         IF(K.NE.L)GOTO15
         CALL CST(1,2,3,TOTALA)
         GOTO 999
      15 CALL CST(1,2,5,AREA)
         TOTALA=TOTALA+AREA
         CALL CST(2,3,5,AREA)
         TOTALA=TOTALA+AREA
         CALL CST(3,4,5,AREA)
         TOTALA=TOTALA+AREA
         CALL CST(4,1,5,AREA)
         TOTALA=TOTALA+AREA
     999 RETURN
         END
         SUBROUTINE CST(I,J,K,AREA)
C           IMPLICIT REAL*8(A-H,O-Z)
         IMPLICIT REAL(A-H,O-Z)
         DIMENSION CB(3,6),LC(6),LT(3),TK(6,6)
C
         COMMON/CONS/NNP,NEL,NMAT,NSLC,NOPT,NBODY,MTYP,NCKEL
         COMMONE(10),PR(10),RO(10),TH(10),X(700),Y(700)
         COMMON/ONE/QK(10,10),Q(10),B(3,10),C(3,3),BT(3,6),XQ(5),YQ(5)
         COMMON/TWO/IBAND,NEQ,R(1400),AK(1400,100)
         LT(1)=I
         LT(2)=J
         LT(3)=K
C        COMPUTE  STRAIN-DISPLACEMENT MATRIX B FOR TRIANGLE, EQ, (5-35A)
         BT(1,1)=YQ(J)-YQ(K)
         BT(1,2)=YQ(K)-YQ(I)
         BT(1,3)=YQ(I)-YQ(J)
         BT(2,4)=XQ(K)-XQ(J)
         BT(2,5)=XQ(I)-XQ(K)
         BT(2,6)=XQ(J)-XQ(I)
         BT(3,1)=BT(2,4)
         BT(3,2)=BT(2,5)
         BT(3,3)=BT(2,6)
         BT(3,4)=BT(1,1)
         BT(3,5)=BT(1,2)
         BT(3,6)=BT(1,3)
         AREA=(BT(2,4)*BT(1,3)-BT(2,6)*BT(1,1))/2.0
C
C  COMPUTE   C*B
         DO 101I=1,3
         DO 10JJ=1,6
         CB(II,JJ)=0.0
         DO 10KK=1,3
      10 CB(II,JJ)=CB(II,JJ)+C(II,KK)*BT(KK,JJ)
C
C  COMPUTE (B**T)*C*B, EQ,(5-45A)
         DO 121I=1,6
         DO 12JJ=1,6
         TK(II,JJ)=0.0
         DO 12KK=1,3
      12 TK(II,JJ)=TK(II,JJ)+BT(KK,II)*CB(KK,JJ)
C
C  ADD TRIANGLE STIFNESS TO QUADRILATERAL STIFFNESS, EX,(6-2),
C  ADD TRIANGLE STRAIN-DISPLACEMENT MATRIX TO QUADRILATERAL  STRAIN-
C  DISPLACEMENT MATRIX
         DO 151I=1,3
         LC(II)=2*LT(II)-1
      15 LC(II+3)=2*LT(II)
         DO 301I=1,6
         LL=LC(II)
         FK=1.0/(4.0*AREA)
         FB=2.0*FK
         DO 20JJ=1,6
         MM=LC(JJ)
```

```
      20 QK(LL,MM)=QK(LL,MM)+TK(II,JJ)*TH(MTYP)*FK
         DO 30JJ=1,3
      30 B(JJ,LL)=B(JJ,LL)+BT(JJ,II)*FB
C
C  DEVELOP  BODY  FORCE  VECTOR,  EQ,(5-61B)
         IF(NBODY.EQ.0)GOTO999
         TBODYF=AREA*RO(MTYP)*TH(MTYP)
         BODYF=-TBODYF/3.0
         DO 35II=1,3
         JJ=2*LT(II)
      35 Q(JJ)=Q(JJ)+BODYF
     999 RETURN
         END
         SUBROUTINE CRACK
C         IMPLICIT REAL*8 (A-H,O-Z)
         IMPLICIT REAL(A-H,O-Z)
         COMMON/CONS/NNP,NEL,NMAT,NSLC,NOPT,NBODY,MTYP,NCKEL
         COMMONE(10),PR(10),RO(10),TH(10),X(700),Y(700)
         COMMON/TWO/IBAND,NEQ,R(1400),AK(1400,100)
         COMMON/T3/BCR(2,18),EK(171),XXY(18),KCRK(9),LP(18)
         READ(15,12)KEY,MATYP,XC,YC,NCONT
      12 FORMAT(2I5,2F10.0,I5)
         IF(KEY.EQ.1)GOTO10
         NODE=9
         NOE=18
         GOTO 20
      10 NODE=5
         NOE=10
      20 READ(15,2)(KCRK(I),I=1,NODE),MAXDIF
       2 FORMAT(10I5)
         K=2*(MAXDIF+1)
         IF(K.LE.IBAND)GOTO91
         L=IBAND+1
         DO 100I=1,NEQ
         DO 100J=L,K
     100 AK(I,J)=0.
         IBAND=MAXO(IBAND,K)
      91 CONTINUE
         DO 30I=1,NODE
         XXY(2*I-1)=X(KCRK(I))
      30 XXY(2*I)=Y(KCRK(I))
         DO 31I=1,NOE
      31 WRITE(16,32)I,XXY(I)
      32 FORMAT("0",5X,"XXY(",I3,")=",G20.6)
         SMU=E(MATYP)/(2.*(1.+PR(MATYP)))
         IF(NOPT.EQ.1)GOTO40
         ETA=(3.-PR(MATYP))/(1.+PR(MATYP))
         GOTO 50
      40 ETA=3.-4.*PR(MATYP)
      50 CONTINUE
         WRITE(16,35)SMU,ETA
      35 FORMAT("0",5X,"SMU ETA =",2G20.6)
         CALL HYBRID(KEY,SMU,ETA,XC,YC,NCONT)
         DO 60I=1,NODE
         LP(2*I-1)=2*KCRK(I)-1
      60 LP(2*I)=2*KCRK(I)
         DO 36I=1,NOE
      36 WRITE(16,33)I,LP(I)
      33 FORMAT("0",5X,"LP (",I3,")=",I5)
         DO 70LL=1,NOE
         I=LP(LL)
         DO 70MM=1,NOE
         J=LP(MM)-I+1
         IF(J.LE.0)GOTO70
         CALL LOC(LL,MM,IJ,NOE,NOE,1)
         AK(I,J)=AK(I,J)+EK(IJ)
         WRITE(16,84)IJ,EK(IJ),I,J,AK(I,J)
      84 FORMAT("0",5X,"EK(",I4,")=",G20.6,"AK(",I3,",",I3,")=",G20.6)
      70 CONTINUE
         WRITE(16,34)NODE,NOE,MATYP,XC,YC
      34 FORMAT("0",5X,"NODE NOE MATYP XC,YC =",3I4,2G15.5)
         KK=(NOE+1)*NOE/2
         WRITE(12)KK,NODE,NOE,KEY,(LP(I),I=1,NOE),(EK(I),I=1,KK),((BCR(I,
        +J),I=1,KEY),J=1,NOE),XC,YC,MATYP,(KCRK(I),I=1,NODE)
         RETURN
         END
         SUBROUTINE LOC(I,J,IR,N,M,MS)
         IX=I
         JX=J
         IF(MS-1)10,20,30
      10 IRX=N*(JX-1)+IX
         GOTO 36
      20 IF(IX-JX)22,24,24
      22 IRX=IX+(JX*JX-JX)/2
         GOTO 36
      24 IRX=JX+(IX*IX-IX)/2
         GOTO 36
      30 IRX=0
         IF(IX-JX)36,32,36
      32 IRX=IX
      36 IR=IRX
         RETURN
         END
         SUBROUTINE HYBRID(KEY,SMU,ETA,XC,YC,NCCNT)
C         IMPLICIT REAL*8(A,B,D-H,O-Y) ,COMPLEX*16(Z,C)
         IMPLICIT REAL(A,B,D-H,O-Y),COMPLEX(Z,C)
         COMPLEX SINT,SJNT
C         COMPLEX*16 ZET,Z,DCMPLX,DCONJG,F1,F2,F3,FF2(32),FF3(32),XY
         COMPLEX ZET,Z,DCMPLX,DCONJG,F1,F2,F3,FF2(32),FF3(32),XY
C         COMPLEX*16  ZETK,CZK,ZETT,CZZ,ZET4,ZE,ZD,ZC,ZA,ZB,CI,CDSQRT
         COMPLEX ZETK,CZK,ZETT,CZZ,ZET4,ZE,ZD,ZC,ZA,ZB,CI,CDSQRT
         DIMENSION VG(32,34),X(5),Y(5),O(5),BK(32,34),VA(136),VI(32,34),
        +VB(136),W(5)
         COMMON/T3/BCR(2,18),EK(171),XXY(18),KCRK(9),LP(18)
         EQUIVALENCE(Z,ZETT),(UX,UXX)
         EQUIVALENCE(VI(1,1),VG(1,1))
         DATA W/.2369269,.4786287,.5688889,.4786287,.2369269/
         DATA Y/-.9061799,-.5384693,0.,.5384693,.9061799/
         DATA NNT/9/
         CI=CMPLX(0.E0,1.E0)
         IF(KEY.EQ.1)NDPE=10
         IF(KEY.EQ.2)NDPE=18
         ELO=1.0
         NT=KEY*NNT
         NNPE=NDPE/2
         IF(NCCNT.EQ.0)GOTO5
         DO 6I=1,NNPE
         I2=I*2
      6  XXY(I2)=-XXY(I2)
      5  CONTINUE
```

```
      NNN=(NNPE-1)/2
      NTT=(NNT*NNT+NNT)/2
      DO 11=1,NTT
      VA(I)=0.
    1 VB(I)=0.
      DO 41=1,NT
      DO 4J=1,NDPE
    4 VG(I,J)=0.
C     INTEGRATION COEFFICIENTS
      DO 111=1,5
      X(I)=(1.+Y(I))/2.
   11 G(I)=W(I)/2.
      ISIDE=NNPE/KEY+KEY/2
      ES=SQRT((XXY(1)-XC)**2+(XXY(2)-YC)**2)
      UXX=(XXY(2)-YC)/ES
      UY=(XXY(1)-XC)/ES
      DO 4401=1,ISIDE
      II=I+I
      XXY(II-1)=(XXY(II-1)-XC)/ES
      XXY(II)=(XXY(II)-YC)/ES
      XT=XXY(II-1)*UY+XXY(II)*UXX
      XXY(II)=-XXY(II-1)*UXX+XXY(II)*UY
  440 XXY(II-1)=XT
      ISIDE=NNPE/KEY-1/KEY
      DO 411SI=1,ISIDE
      IY=ISI+ISI
      UXX=XXY(IY+2)-XXY(IY)
      UY=XXY(IY-1)-XXY(IY+1)
      DO 4111=1,5
      XX=XXY(IY-1)+(1.-X(III))+XXY(IY+1)*X(III)
      YY=XXY(IY)+(1.-X(III))+XXY(IY+2)*X(II)
      Z=CMPLX(XX,YY)
      ZET=CSQRT(ZETT)
      ZET4=ZETT=ZETT
      CZZ=CONJG(ZETT)
      ZETK=1./ZET4
      KK=1
      IF(KEY.EQ.2)GOTO1011
      DO 1010K=1,NNT
      FF2(K)=0.
      ZETK=ZETK*ZET
      CZK=CONJG(ZETK)
      KK=-KK
      IF(UY.EQ.0.)GOTO1009
      ZD=CZK*CZZ-KK*ZETK*ZETT
      ZC=ZETK*(CZZ-ZETT)
      FF2(K)=0.5*K*(K-2)*ZC+K*ZD
      FF2(K)=FF2(K)+UY*.5
 1009 ZE=CZK*CZZ*(CZZ-ZETT)
      FF3(K)=ETA*ZETK*ZET4+KK*CZK*CONJG(ZET4)+.5*K*ZE
      FF3(K)=FF3(K)*.25
      IF(UX.EQ.0.)GOTO1010
      IB=K+2+KK+KK
      ZA=(K-2)*ZETK-2.*CZK
      FF2(K)=-K*(CZZ*ZA-IB*ZETK*ZETT)*CI*.25*UX+FF2(K)
 1010 CONTINUE
      GOTO 2000
 1011 DO 1012K=1,NNT
      FF2(K)=0.
      FF2(K+NNT)=0.
      ZETK=ZETK*ZET
      CZK=CONJG(ZETK)
      KK=-KK
      IF(UY.EQ.0.)GOTO1014
      ZD=CZK*CZZ-KK*ZETK*ZETT
      ZC=ZETK*(CZZ-ZETT)
      FF2(K)=.5*K*(K-2)*ZC+K*ZD
      FF2(K)=FF2(K)+UY*.5
      FF2(K+NNT)=(FF2(K)-K*ZD*UY)*CI
 1014 ZE=CZK*CZZ*(CZZ-ZETT)
      FF3(K)=ETA*ZETK*ZET4+KK*CZK*CONJG(ZET4)+.5*K*ZE
      FF3(K)=FF3(K)*.25
      FF3(K+NNT)=(FF3(K)-.25*K*ZE)*CI
      IF(UX.EQ.0.)GOTO1012
      IB=K+2+KK+KK
      ZA=(K-2)*ZETK-2.*CZK
      FF2(K)=-K*(CZZ*ZA-IB*ZETK*ZETT)*CI*.25*UX+FF2(K)
      IB=K+2-KK-KK
      ZA=(K-2)*ZETK+2.*CZK
      FF2(K+NNT)=K*(CZZ*ZA-IB*ZETK*ZETT)*.25*UX+FF2(K+NNT)
 1012 CONTINUE
 2000 KJ=0
      DO 41K=1,NNT
      L=2*ISI-1
      DO 40J=1,KEY
      I=J=NNT-NNT+K
      SINT=FF2(I)*X(II)
      SJNT=FF2(I)-SINT
      VG(I,L)=VG(I,L)+G(II)*AIMAG(SJNT)
      VG(I,L+1)=VG(I,L+1)+G(II)*REAL(SJNT)
      VG(I,L+2)=VG(I,L+2)+G(II)*AIMAG(SINT)
   40 VG(I,L+3)=VG(I,L+3)+G(II)*REAL(SINT)
      DO 41J=1,K
      SINT=FF2(K)*FF3(J)+FF2(J)*FF3(K)
      KJ=KJ+1
      VA(KJ)=VA(KJ)+G(II)*AIMAG(SINT)/SMU
      IF(KEY.EQ.1)GOTO41
      I=K+NNT
      L=J+NNT
      SINT=FF2(I)*FF3(L)+FF2(L)*FF3(I)
      VB(KJ)=VB(KJ)+G(II)*AIMAG(SINT)/SMU
   41 CONTINUE
      IF(KEY.EQ.1)GOTO64
      DO 500III=1,NNT
      VG(III,2)=0.
      VG(III,1)=2.*VG(III,1)
      II=III+NNT
      VG(II,2)=2.*VG(II,2)
      VG(II,1)=0.
      DO 455J=1,NNN
      JU=J+1
      JL=NNPE+1-J
      VG(III,2*JL-1)=VG(III,2*JU-1)
      VG(III,2*JL)=-VG(III,2*JU)
      VG(II,2*JL-1)=-VG(II,2*JU-1)
  455 VG(II,2*JL)=VG(II,2*JU)
  500 CONTINUE
      DO 501I=1,NDPE
  501 VG(NNT+2,I)=0.
      DO 631=1,NTT
```

```
      VA(I)=VA(I)*2.
   63 VB(I)=VB(I)*2.
      VB(2)=0.
      VB(3)=1.
      DO 62 I=3,NNT
   62 VB((I*I-1)/2+2)=0.
      64 CONTINUE
      CALL SINV(VA,NNT,.1E-05,IER)
      IF(KEY.EQ.2)CALLSINV(VB,NNT,.1E-05,IEE)
      DO 111 J=1,NDPE
      DO 110 I=1,NNT
      II=(I*I-1)/2
      BK(I,J)=0.
      DO 110 K=1,NNT
      IK=II+K
      IF(K.GT.I)IK=(K*K-K)/2+I
  110 BK(I,J)=BK(I,J)+VA(IK)*VI(K,J)
      IF(KEY.EQ.1)GOTO111
      JJ=NNT+1
      DO 121 I=II,NT
      IJ=I-NNT
      IJ=(IJ*IJ-IJ)/2
      BK(I,J)=0.
      DO 121 K=1,NNT
      IK=IJ+K
      IF(K.GT.I-NNT)IK=(K*K-K)/2+I-NNT
  121 BK(I,J)=BK(I,J)+VB(IK)*VI(K+NNT,J)
  111 CONTINUE
      IJ=0
      DO 112 I=1,NDPE
      DO 112 J=1,I
      IJ=IJ+1
      EK(IJ)=0.
      DO 112 K=1,NT
  112 EK(IJ)=EK(IJ)+BK(K,J)*VI(K,I)
      ELG=SQRT(2./ES)
      DO 113 J=1,NDPE
      BCR(2,J)=0.
      IF(KEY.EQ.2)BCR(2,J)=ELG*BK(10,J)
  113 BCR(1,J)=ELG*BK(1,J)
      RETURN
      END
      SUBROUTINE SIFAC(M,TOTAL)
C       IMPLICIT REAL*8 (A-H,O-Z)
      IMPLICIT REAL(A-H,O-Z)
C       REAL*8  K1,K2
      REAL K1,K2
      COMMON/TWO/IBAND,NEQ,R(1400),AK(1400,100)
      COMMON/T3/BCR(2,18),EK(171),XXY(18),KCRK(9),LP(18)
      WRITE(16,35)M
   35 FORMAT("0",5X,"CKEL =",I5,/)
      READ(12)KK,NODE,NOE,KEY,(LP(I),I=1,NOE),(EK(I),I=1,KK),((BCR(I,J)
     *,I=1,KEY),J=1,NOE),XC,YC,MATYP,(KCRK(I),I=1,NODE)
      TOTAL=0.
      K1=0.
      K2=0.
      DO 20 I=1,NOE
      K1=K1+BCR(1,I)*R(LP(I))
      IF(KEY.EQ.1)GOTO20
      K2=K2+BCR(2,I)*R(LP(I))
   20 CONTINUE
      PI=3.1415926
      K1=K1*SQRT(PI)
      K2=K2*SQRT(PI)
      WRITE(16,1)M,K1,K2
    1 FORMAT("-",5X,"... STRESS INTENSIYY FACTOR ...",I2,/,"0",5X,
     +"OPENING  MODE K1 = ",G20.6,/,"0",5X,"SHEARING MODE K2 = ",G20.
     +6)
      WRITE(16,100)XC,YC,MATYP
  100 FORMAT("0",5X,"CRACK TIP  XC =",G16.6," YC =",G16.6,
     +"  AT MATERIAL",I4)
      WRITE(16,200)NODE,(KCRK(I),I=1,NODE)
  200 FORMAT("0",5X,"THE",I4,"NODES =",10I4)
      W=0.
      DO 30 I=1,NOE
      XXY(I)=0.
      DO 30 J=1,NOE
      CALL LOC(I,J,IJ,NOE,NOE,1)
   30 XXY(I)=XXY(I)+R(LP(J))*EK(IJ)*.5
      DO 40 I=1,NOE
   40 W=W+XXY(I)*R(LP(I))
      WRITE(16,2)W
    2 FORMAT("0",5X,"STRAIN ENERGY =",G16.6)
      TOTAL=TOTAL+W
      WRITE(16,300)
  300 FORMAT("0",10X," * * * * * * * * * * * * * * * * * * * * ",//)
      RETURN
      END
      SUBROUTINE GEOMBC(U,N)
C       IMPLICIT REAL*8(A-H,O-Z)
      IMPLICIT REAL(A-H,O-Z)
      COMMON/TWO/IBAND,NEQ,R(1400),AK(1400,100)
C  THIS SUBROUTINE MODIFIES THE ASSEMBLAGE STIFFNESS AND LOADS FOR THE
C  PRESCRIBED DISPLACEMENT U AT DEGREE OF FREEDOM N, EQ.(6-18B). (REF.1)
      DO 100M=2,IBAND
      K=N-M+1
      IF(K.LE.0)GOTO50
      R(K)=R(K)-AK(K,M)*U
      AK(K,M)=0.0
   50 K=N+M-1
      IF(K.GT.NEQ)GOTO100
      R(K)=R(K)-AK(N,M)*U
      AK(N,M)=0.0
  100 CONTINUE
      AK(N,1)=1.0
      R(N)=U
      RETURN
      END
      SUBROUTINE STRESS(WORK)
C       IMPLICIT REAL*8(A-H,O-Z)
      IMPLICIT REAL(A-H,O-Z)
      DIMENSION SIG(6)
C
      COMMON/CONS/NNP,NEL,NMAT,NSLC,NOPT,NBODY,MTYP,NCKEL
      COMMONE(10),PR(10),RO(10),TH(10),X(700),Y(700)
      COMMON/ONE/QK(10,10),Q(10),B(3,10),C(3,3),BT(3,6),XQ(5),YQ(5)
      COMMON/TWO/IBAND,NEQ,R(1400),AK(1400,100)
      COMMON/T1/IE(700,5)
      REWIND 11
      REWIND 13
```

```
      WRITE(16,300)
      WORK=0.0
      NOLINE=47
C
C  RETRIEVE MULTIPLIERS, PIVOTS, MATRICES B AND C, AND CENTROIDAL COORD,
C  FOR ELEMENT
      DO 5M=1,NEL
      READ(11)((QK(I,J),J=1,10),I=1,2),Q(9),Q(10),((B(I,J),J=1,10),I=1,
     +3),((C(I,J),J=1,3),I=1,3),XC,YC
C
C  SELECT NODAL DISPLACEMENTS FOR THE ELEMENT
      LIM=4
      IF(IE(M,3).EQ.IE(M,4))LIM=3
      DO 10I=1,LIM
      II=2*I
      JJ=2*IE(M,I)
      Q(II-1)=R(JJ-1)
   10 Q(II)=R(JJ)
C
C  RECOVER CONDENSED DISPLACEMENTS FOR THE QUADRILATERAL, EQ. (5-64G)
      IF(LIM.EQ.3)GOTO16
      DO 15K=1,2
      JK=K+8
      IK=JK-1
      DO 15L=1,IK
   15 Q(JK)=Q(JK)-QK(K,L)*Q(L)
C
C  COMPUTE ELEMENT STRAINS, EQ.(5-35A)
      LIM=10
      FAC=0.25
      GOTO 17
   16 LIM=6
      FAC=1.0
   17 DO 20I=1,3
      E(I)=0.0
      DO 20J=1,LIM
   20 E(I)=E(I)+B(I,J)*Q(J)*FAC
C
C COMPUTE STRAIN ENERGY IN EACH ELEMENT
      READ(13)KK,((QK(I,J),J=1,KK),I=1,KK)
      DO 40I=1,KK
      RO(I)=0.0
      DO 40J=1,KK
   40 RO(I)=RO(I)+0.5*Q(J)*QK(I,J)
      W=0.0
      DO 50I=1,KK
   50 W=W+RO(I)*Q(I)
      WORK=WORK+W
C
C  COMPUTE ELEMENT STRESSES  , EQ.(5-35B)
      DO 30I=1,3
      SIG(I)=0.0
      DO 30J=1,3
   30 SIG(I)=SIG(I)+C(I,J)*E(J)
C  COMPUTE PRINCIPAL STRESSES AND THE ANGLE WITH THE POSITIVE X AXIS
      SP=(SIG(1)+SIG(2))/2.0
      SM=(SIG(1)-SIG(2))/2.0
      DS=SQRT(SM*SM+SIG(3)*SIG(3))
      SIG(4)=SP+DS
      SIG(5)=SP-DS
      SIG(6)=0.0
      IF(SIG(3).NE.0.0.AND.SM.NE.0.0)SIG(6)=28.648*ATAN2(SIG(3),SM)
C  PRINT STRESSES, 50 LINES PER PAGE
      IF(NOLINE.GT.0)GOTO54
      WRITE(16,1000)
      NOLINE=49
   54 NOLINE=NOLINE-1
    5 WRITE(16,1010)M,XC,YC,(SIG(I),I=1,6)
      WRITE(16,21)WORK
   21 FORMAT("-",5X," . . .STRAIN ENERGY W/O CKEL=",G20.6," . . .")
      ENDFILE11
  300 FORMAT("1OUTPUT TABLE 2.. STRESSES AT ELEMENT CENTROIDS"//1X,
     +"ELEMENT",9X,"X",9X,"Y",4X,"SIGMA(X)",4X,"SIGMA(Y)",4X,
     +"TAU(X,Y)",4X,"SIGMA(1)",4X,"SIGMA(2)",7X,"ANGLE")
 1000 FORMAT("1","ELEMENT",9X,"X",9X,"Y",4X,"SIGMA(X)",4X,
     +"SIGMA(Y)",4X,"TAU(X,Y)",4X,"SIGMA(1)",4X,"SIGMA(2)",7X,
     +"ANGLE")
 1010 FORMAT(I8,2F10.2,1P6E12.4)
      RETURN
      END
      SUBROUTINE BANSOL(A,B,NEQ,NBAND,MAXDOF,MAXBW)
C       IMPLICIT REAL*8 (A-H,O-Z)
      IMPLICIT REAL(A-H,O-Z)
      DIMENSION A(MAXDOF,MAXBW),B(1)
      DO 10N=1,NEQ
      I=N
      DO 20L=2,NBAND
      I=I+1
      IF(A(N,L).EQ.0.)GOTO20
      C=A(N,L)/A(N,1)
      J=0
      DO 30K=L,NBAND
      J=J+1
      IF(A(N,K).EQ.0.)GOTO30
      A(I,J)=A(I,J)-C*A(N,K)
   30 CONTINUE
      A(N,L)=C
C       REDUCEL LOAD VECTOR
      B(I)=B(I)-C*B(N)
   20 CONTINUE
   10 B(N)=B(N)/A(N,1)
C       BACK SUBSTITUTION
      N=NEQ
   35 N=N-1
      IF(N.LE.0)GOTO43
      L=N
      DO 40K=2,NBAND
      L=L+1
      IF(A(N,K).EQ.0.)GOTO40
      B(N)=B(N)-A(N,K)*B(L)
   40 CONTINUE
      GOTO 35
   43 RETURN
      END
      SUBROUTINE SINV(A,N,EPS,IER)
C       REAL*8 A(1) ,  APS,DIN,WORK
      REAL A(1),APS,DIN,WORK
      CALL MFSD(A,N,EPS,IER)
      IF(IER)9,1,1
    1 IPIV=N*(N+1)/2
```

```
      IND=IPIV
      DO 6 I=1,N
      DIN=1.E0/DBLE(A(IPIV))
      A(IPIV)=DIN
      MIN=N
      KEND=I-1
      LANF=N-KEND
      IF(KEND)5,5,2
    2 J=IND
      DO 4 K=1,KEND
      WORK=0.E0
      MIN=MIN-1
      LHOR=IPIV
      LVER=J
      DO 3 L=LANF,MIN
      LVER=LVER+1
      LHOR=LHOR+L
    3 WORK=WORK+DBLE(A(LVER))*A(LHOR))
      A(J)=-WORK*DIN
    4 J=J-MIN
    5 IPIV=IPIV-MIN
    6 IND=IND-1
      DO 8 I=1,N
      IPIV=IPIV+I
      J=IPIV
      DO 8 K=I,N
      WORK=0.E0
      LHOR=J
      DO 7 L=K,N
      LVER=LHOR+K-I
      WORK=WORK+DBLE(A(LHOR))*A(LVER))
    7 LHOR=LHOR+L
      A(J)=WORK
    8 J=J+K
    9 RETURN
      END
      SUBROUTINE MFSD(A,N,EPS,IER)
C       REAL*8 A(1),EPS,TOL
      REAL A(1),EPS,TOL
C       REAL*8 DPIV,DSUM
      REAL DPIV,DSUM
      IF(N-1)12,1,1
    1 IER=0
      KPIV=0
      DO 11 K=1,N
      KPIV=KPIV+K
      IND=KPIV
      LEND=K-1
      TOL=ABS(EPS*A(KPIV))
      DO 11 I=K,N
      DSUM=0.E0
      IF(LEND)2,4,2
    2 DO 3 L=1,LEND
      LANF=KPIV-L
      LIND=IND-L
    3 DSUM=DSUM+DBLE(A(LANF)*A(LIND))
    4 DSUM=DBLE(A(IND) -DSUM)
      IF(I-K)10,5,10
    5 IF((DSUM)-TOL)6,6,9
    6 IF(DSUM)12,12,7
    7 IF(IER)8,8,9
    8 IER=K-1
    9 DPIV=SQRT(DSUM)
      A(KPIV)=DPIV
      DPIV=1.E0/DPIV
      GOTO 11
   10 A(IND)=DSUM=DPIV
   11 IND=IND+I
      RETURN
   12 IER=-1
      RETURN
      END
```

Sample Input for Finite Element Fracture Program- The following pages contain the input cards necessary to run the finite element program.

```
 1      1      PHASE 2 MESH, TIP= 53.5
 2    615   565     3     7     1     0     1
 3 800000.0   0.35        0.0         1.0
 4 9000.0     0.35        0.0         1.0
 5 350000.0   0.35        0.0         1.0
 6      1     3 0.0       0.0         0.0         0.0
 7      2     3 8.0       0.0         0.0         0.0
 8      3     3 16.0      0.0         0.0         0.0
 9      4     3 24.0      0.0         0.0         0.0
10      5     3 30.0      0.0         0.0         0.0
11      6     3 36.0      0.0         0.0         0.0
12      7     3 42.0      0.0         0.0         0.0
13      8     3 46.0      0.0         0.0         0.0
14      9     3 50.0      0.0         0.0         0.0
15     10     3 54.0      0.0         0.0         0.0
16     11     3 58.0      0.0         0.0         0.0
17     12     3 60.0      0.0         0.0         0.0
18     13     3 62.0      0.0         0.0         0.0
19     14     3 64.0      0.0         0.0         0.0
20     15     3 66.0      0.0         0.0         0.0
21     16     3 67.0      0.0         0.0         0.0
22     17     3 68.0      0.0         0.0         0.0
23     18     3 68.5      0.0         0.0         0.0
24     19     3 69.0      0.0         0.0         0.0
25     20     3 69.3      0.0         0.0         0.0
26     21     3 69.75     0.0         0.0         0.0
27     22     3 69.95     0.0         0.0         0.0
28     23     3 0.0       8.0         0.0         0.0
29     26     0 24.0      8.0         0.0         0.0
30     29     0 42.0      8.0         0.0         0.0
31     33     0 58.0      8.0         0.0         0.0
32     37     0 66.0      8.0         0.0         0.0
33     39     0 68.0      8.0         0.0         0.0
34     41     0 69.0      8.0         0.0         0.0
35     42     0 69.3      8.0         0.0         0.0
36     43     0 69.75     8.0         0.0         0.0
37     44     1 69.95     8.0         0.0         0.0
38     45     3 0.0       16.0        0.0         0.0
39     48     0 24.0      16.0        0.0         0.0
40     51     0 42.0      16.0        0.0         0.0
41     55     0 58.0      16.0        0.0         0.0
42     59     0 66.0      16.0        0.0         0.0
43     61     0 68.0      16.0        0.0         0.0
44     63     0 69.0      16.0        0.0         0.0
45     64     0 69.3      16.0        0.0         0.0
46     65     0 69.75     16.0        0.0         0.0
47     66     1 69.95     16.0        0.0         0.0
48     67     3 0.0       22.0        0.0         0.0
49     70     0 24.0      22.0        0.0         0.0
50     73     0 42.0      22.0        0.0         0.0
51     77     0 58.0      22.0        0.0         0.0
52     81     0 66.0      22.0        0.0         0.0
53     83     0 68.0      22.0        0.0         0.0
54     85     0 69.0      22.0        0.0         0.0
55     86     0 69.3      22.0        0.0         0.0
56     87     0 69.75     22.0        0.0         0.0
57     88     1 69.95     22.0        0.0         0.0
58     89     3 0.0       28.0        0.0         0.0
59     92     0 24.0      28.0        0.0         0.0
60     95     0 42.0      28.0        0.0         0.0
```

61	99	0	58.0	28.0	0.0	0.0
62	103	0	66.0	28.0	0.0	0.0
63	105	0	68.0	28.0	0.0	0.0
64	107	0	69.0	28.0	0.0	0.0
65	108	0	69.3	28.0	0.0	0.0
66	109	0	69.75	28.0	0.0	0.0
67	110	1	69.95	28.0	0.0	0.0
68	111	3	0.0	34.0	0.0	0.0
69	114	0	24.0	34.0	0.0	0.0
70	117	0	42.0	34.0	0.0	0.0
71	121	0	58.0	34.0	0.0	0.0
72	125	0	66.0	34.0	0.0	0.0
73	127	0	68.0	34.0	0.0	0.0
74	129	0	69.0	34.0	0.0	0.0
75	130	0	69.3	34.0	0.0	0.0
76	131	0	69.75	34.0	0.0	0.0
77	132	1	69.95	34.0	0.0	0.0
78	133	3	0.0	40.0	0.0	0.0
79	136	0	24.0	40.0	0.0	0.0
80	139	0	42.0	40.0	0.0	0.0
81	143	0	58.0	40.0	0.0	0.0
82	147	0	66.0	40.0	0.0	0.0
83	149	0	68.0	40.0	0.0	0.0
84	151	0	69.0	40.0	0.0	0.0
85	152	0	69.3	40.0	0.0	0.0
86	153	0	69.75	40.0	0.0	0.0
87	154	1	69.95	40.0	0.0	0.0
88	155	3	0.0	44.0	0.0	0.0
89	158	0	24.0	44.0	0.0	0.0
90	161	0	42.0	44.0	0.0	0.0
91	165	0	58.0	44.0	0.0	0.0
92	169	0	66.0	44.0	0.0	0.0
93	171	0	68.0	44.0	0.0	0.0
94	173	0	69.0	44.0	0.0	0.0
95	174	0	69.3	44.0	0.0	0.0
96	175	0	69.75	44.0	0.0	0.0
97	176	1	69.95	44.0	0.0	0.0
98	177	3	0.0	46.0	0.0	0.0
99	180	0	24.0	46.0	0.0	0.0
100	183	0	42.0	46.0	0.0	0.0
101	187	0	58.0	46.0	0.0	0.0
102	191	0	66.0	46.0	0.0	0.0
103	193	0	68.0	46.0	0.0	0.0
104	195	0	69.0	46.0	0.0	0.0
105	196	0	69.3	46.0	0.0	0.0
106	197	0	69.75	46.0	0.0	0.0
107	198	1	69.95	46.0	0.0	0.0
108	199	3	0.0	48.0	0.0	0.0
109	202	0	24.0	48.0	0.0	0.0
110	205	0	42.0	48.0	0.0	0.0
111	209	0	58.0	48.0	0.0	0.0
112	213	0	66.0	48.0	0.0	0.0
113	215	0	68.0	48.0	0.0	0.0
114	217	0	69.0	48.0	0.0	0.0
115	218	0	69.3	48.0	0.0	0.0
116	219	0	69.75	48.0	0.0	0.0
117	220	1	69.95	48.0	0.0	0.0
118	221	3	0.0	49.0	0.0	0.0
119	224	0	24.0	49.0	0.0	0.0
120	227	0	42.0	49.0	0.0	0.0

121	231	0	58.0	49.0	0.0	0.0
122	235	0	66.0	49.0	0.0	0.0
123	237	0	68.0	49.0	0.0	0.0
124	239	0	69.0	49.0	0.0	0.0
125	240	0	69.3	49.0	0.0	0.0
126	241	0	69.75	49.0	0.0	0.0
127	242	0	69.95	49.0	0.0	0.0
128	243	3	0.0	50.0	0.0	0.0
129	246	0	24.0	50.0	0.0	0.0
130	249	0	42.0	50.0	0.0	0.0
131	253	0	58.0	50.0	0.0	0.0
132	257	0	66.0	50.0	0.0	0.0
133	259	0	68.0	50.0	0.0	0.0
134	261	0	69.0	50.0	0.0	0.0
135	262	0	69.3	50.0	0.0	0.0
136	263	0	69.75	50.0	0.0	0.0
137	264	0	69.95	50.0	0.0	0.0
138	265	3	0.0	50.833	0.0	0.0
139	268	0	24.0	50.833	0.0	0.0
140	271	0	42.0	50.833	0.0	0.0
141	275	0	58.0	50.833	0.0	0.0
142	279	0	66.0	50.833	0.0	0.0
143	281	0	68.0	50.833	0.0	0.0
144	283	0	69.0	50.833	0.0	0.0
145	284	0	69.3	50.833	0.0	0.0
146	285	0	69.75	50.833	0.0	0.0
147	286	0	69.95	50.833	0.0	0.0
148	287	3	0.0	51.5	0.0	0.0
149	290	0	24.0	51.5	0.0	0.0
150	293	0	42.0	51.5	0.0	0.0
151	297	0	58.0	51.5	0.0	0.0
152	301	0	66.0	51.5	0.0	0.0
153	303	0	68.0	51.5	0.0	0.0
154	305	0	69.0	51.5	0.0	0.0
155	306	0	69.3	51.5	0.0	0.0
156	307	0	69.75	51.5	0.0	0.0
157	308	0	69.95	51.5	0.0	0.0
158	309	3	0.0	51.833	0.0	0.0
159	312	0	24.0	51.833	0.0	0.0
160	315	0	42.0	51.833	0.0	0.0
161	319	0	58.0	51.833	0.0	0.0
162	323	0	66.0	51.833	0.0	0.0
163	325	0	68.0	51.833	0.0	0.0
164	327	0	69.0	51.833	0.0	0.0
165	328	0	69.3	51.833	0.0	0.0
166	329	0	69.75	51.833	0.0	0.0
167	330	0	69.95	51.833	0.0	0.0
168	331	3	0.0	52.167	0.0	0.0
169	334	0	24.0	52.167	0.0	0.0
170	337	0	42.0	52.167	0.0	0.0
171	341	0	58.0	52.167	0.0	0.0
172	345	0	66.0	52.167	0.0	0.0
173	347	0	68.0	52.167	0.0	0.0
174	349	0	69.0	52.167	0.0	0.0
175	350	0	69.3	52.167	0.0	0.0
176	351	0	69.75	52.167	0.0	0.0
177	352	0	69.95	52.167	0.0	0.0
178	353	3	0.0	52.5	0.0	0.0
179	356	0	24.0	52.5	0.0	0.0
180	359	0	42.0	52.5	0.0	0.0

181	363	0	58.0	52.5	0.0	0.0
182	367	0	66.0	52.5	0.0	0.0
183	369	0	68.0	52.5	0.0	0.0
184	371	0	69.0	52.5	0.0	0.0
185	372	0	69.3	52.5	0.0	0.0
186	373	0	69.75	52.5	0.0	0.0
187	374	0	69.95	52.5	0.0	0.0
188	375	3	0.0	52.833	0.0	0.0
189	378	0	24.0	52.833	0.0	0.0
190	381	0	42.0	52.833	0.0	0.0
191	385	0	58.0	52.833	0.0	0.0
192	389	0	66.0	52.833	0.0	0.0
193	391	0	68.0	52.833	0.0	0.0
194	393	0	69.0	52.833	0.0	0.0
195	394	0	69.3	52.833	0.0	0.0
196	395	0	69.75	52.833	0.0	0.0
197	396	0	69.95	52.833	0.0	0.0
198	397	3	0.0	53.25	0.0	0.0
199	400	0	24.0	53.25	0.0	0.0
200	403	0	42.0	53.25	0.0	0.0
201	407	0	58.0	53.25	0.0	0.0
202	411	0	66.0	53.25	0.0	0.0
203	413	0	68.0	53.25	0.0	0.0
204	415	0	69.0	53.25	0.0	0.0
205	416	0	69.3	53.25	0.0	0.0
206	417	0	69.75	53.25	0.0	0.0
207	418	0	69.95	53.25	0.0	0.0
208	419	3	0.0	53.5	0.0	0.0
209	422	0	24.0	53.5	0.0	0.0
210	425	0	42.0	53.5	0.0	0.0
211	429	0	58.0	53.5	0.0	0.0
212	433	0	66.0	53.5	0.0	0.0
213	435	0	68.0	53.5	0.0	0.0
214	437	0	69.0	53.5	0.0	0.0
215	438	0	69.3	53.5	0.0	0.0
216	439	0	69.75	53.5	0.0	0.0
217	440	3	0.0	53.75	0.0	0.0
218	443	0	24.0	53.75	0.0	0.0
219	446	0	42.0	53.75	0.0	0.0
220	450	0	58.0	53.75	0.0	0.0
221	454	0	66.0	53.75	0.0	0.0
222	456	0	68.0	53.75	0.0	0.0
223	458	0	69.0	53.75	0.0	0.0
224	459	0	69.3	53.75	0.0	0.0
225	460	0	69.75	53.75	0.0	0.0
226	461	1	70.0	53.75	0.0	0.0
227	462	3	0.0	54.1	0.0	0.0
228	465	0	24.0	54.1	0.0	0.0
229	468	0	42.0	54.1	0.0	0.0
230	472	0	58.0	54.1	0.0	0.0
231	476	0	66.0	54.1	0.0	0.0
232	478	0	68.0	54.1	0.0	0.0
233	480	0	69.0	54.1	0.0	0.0
234	481	0	69.3	54.1	0.0	0.0
235	482	0	69.75	54.1	0.0	0.0
236	483	1	70.0	54.1	0.0	0.0
237	484	3	0.0	54.5	0.0	0.0
238	487	0	24.0	54.5	0.0	0.0
239	490	0	42.0	54.5	0.0	0.0
240	494	0	58.0	54.5	0.0	0.0

241	498	0	66.0	54.5	0.0	0.0
242	500	0	68.0	54.5	0.0	0.0
243	502	0	69.0	54.5	0.0	0.0
244	503	0	69.3	54.5	0.0	0.0
245	504	0	69.75	54.5	0.0	0.0
246	505	1	70.0	54.5	0.0	0.0
247	506	3	0.0	55.5	0.0	0.0
248	509	0	24.0	55.5	0.0	0.0
249	512	0	42.0	55.5	0.0	0.0
250	516	0	58.0	55.5	0.0	0.0
251	520	0	66.0	55.5	0.0	0.0
252	522	0	68.0	55.5	0.0	0.0
253	524	0	69.0	55.5	0.0	0.0
254	525	0	69.3	55.5	0.0	0.0
255	526	0	69.75	55.5	0.0	0.0
256	527	1	70.0	55.5	0.0	0.0
257	528	3	0.0	56.5	0.0	0.0
258	531	0	24.0	56.5	0.0	0.0
259	534	0	42.0	56.5	0.0	0.0
260	538	0	58.0	56.5	0.0	0.0
261	542	0	66.0	56.5	0.0	0.0
262	544	0	68.0	56.5	0.0	0.0
263	546	0	69.0	56.5	0.0	0.0
264	547	0	69.3	56.5	0.0	0.0
265	548	0	69.75	56.5	0.0	0.0
266	549	1	70.0	56.5	0.0	0.0
267	550	3	0.0	58.0	0.0	0.0
268	553	0	24.0	58.0	0.0	0.0
269	556	0	42.0	58.0	0.0	0.0
270	560	0	58.0	58.0	0.0	0.0
271	564	0	66.0	58.0	0.0	0.0
272	566	0	68.0	58.0	0.0	0.0
273	568	0	69.0	58.0	0.0	0.0
274	569	0	69.3	58.0	0.0	0.0
275	570	0	69.75	58.0	0.0	0.0
276	571	1	70.0	58.0	0.0	0.0
277	572	3	0.0	59.5	0.0	0.0
278	575	0	24.0	59.5	0.0	0.0
279	578	0	42.0	59.5	0.0	0.0
280	582	0	58.0	59.5	0.0	0.0
281	586	0	66.0	59.5	0.0	0.0
282	588	0	68.0	59.5	0.0	0.0
283	590	0	69.0	59.5	0.0	0.0
284	591	0	69.3	59.5	0.0	0.0
285	592	0	69.75	59.5	0.0	0.0
286	593	1	70.0	59.5	0.0	0.0
287	594	3	0.0	61.0	0.0	0.0
288	597	0	24.0	61.0	0.0	0.0
289	600	0	42.0	61.0	0.0	0.0
290	604	0	58.0	61.0	0.0	0.0
291	608	0	66.0	61.0	0.0	0.0
292	610	0	68.0	61.0	0.0	0.0
293	612	0	69.0	61.0	0.0	0.0
294	613	0	69.3	61.0	0.0	0.0
295	614	0	69.75	61.0	0.0	0.0
296	615	1	70.0	61.0	0.0	0.0

297	1	1	2	24	23	2
298	21	21	22	44	43	2
299	22	23	24	46	45	2
300	42	43	44	66	65	2

```
301    43    45    46    68    67     2
302    63    65    66    88    87     2
303    64    67    68    90    89     2
304    84    87    88   110   109     2
305    85    89    90   112   111     2
306   105   109   110   132   131     2
307   106   111   112   134   133     2
308   126   131   132   154   153     2
309   127   133   134   156   155     2
310   147   153   154   176   175     2
311   148   155   156   178   177     2
312   168   175   176   198   197     2
313   169   177   178   200   199     2
314   189   197   198   220   219     2
315   190   199   200   222   221     2
316   210   219   220   242   241     2
317   211   221   222   244   243     2
318   231   241   242   264   263     2
319   232   243   244   266   265     1
320   252   263   264   286   285     1
321   253   265   266   288   287     1
322   273   285   286   308   307     1
323   274   287   288   310   309     1
324   294   307   308   330   329     1
325   295   309   310   332   331     1
326   315   329   330   352   351     1
327   316   331   332   354   353     1
328   336   351   352   374   373     1
329   337   353   354   376   375     1
330   357   373   374   396   395     1
331   358   375   376   398   397     1
332   378   395   396   418   417     1
333   379   397   398   420   419     1
334   398   416   417   439   438     1
335   399   419   420   441   440     1
336   418   438   439   460   459     1
337   419   440   441   463   462     1
338   439   460   461   483   482     1
339   440   462   463   485   484     1
340   460   482   483   505   504     1
341   461   484   485   507   506     1
342   481   504   505   527   526     1
343   482   506   507   529   528     1
344   502   526   527   549   548     1
345   503   528   529   551   550     1
346   523   548   549   571   570     1
347   524   550   551   573   572     3
348   544   570   571   593   592     3
349   545   572   573   595   594     3
350   565   592   593   615   614     3
351   264   286 1129.44   927.743   0.0        0.0
352   286   308 927.743   765.90    0.0        0.0
353   308   330 765.90    685.113   0.0        0.0
354   330   352 685.113   604.327   0.0        0.0
355   352   374 604.327   523.54    0.0        0.0
356   374   396 523.54    442.753   0.0        0.0
357   396   418 442.753   341.77    0.0        0.0
358     1     1 70.0      53.5              0
359   417   418   461   460   439    44
360     0
```

Sample Outupt From Finite Element Fracture Program - The following pages contain the output from the finite element program run using the sample data.

PROBLEM 1.. PHASE MESH, P= 53.

INPUT TABLE 1.. BASIC PARAMETERS

NUMBER OF NODAL POINTS.	615
NUMBER OF ELEMENTS.	565
NUMBER OF DIFFERENT MATERIALS	3
NUMBER OF SURFACE LOAD CARDS.	7
1 = PLANE STRAIN, 2 = PLANE STRESS. . .	1
BODY FORCES(1 = IN -Y DIREC., 0 = NONE)	0
NUMBER OF CRACK ELEMENTS. . .	1

INPUT TABLE 2.. MATERIAL PROPERTIES

MATERIAL NUMBER	MODULUS OF ELASTICITY	POISSON'S RATIO	MATERIAL DENSITY	MATERIAL THICKNESS
1	0.8000E+06	0.3500E+00	0.0000E+01	0.1000E+01
2	0.9000E+04	0.3500E+00	0.0000E+01	0.1000E+01
3	0.3500E+06	0.3500E+00	0.0000E+01	0.1000E+01

INPUT TABLE 3. NODAL POINT DATA

NODAL POINT	TYPE	X	Y	X-DISP. OR LOAD	Y-DISP. OR LOAD
1	3	0.0000E+01	0.0000E+01	0.0000E+01	0.0000E+01
2	3	0.8000E+01	0.0000E+01	0.0000E+01	0.0000E+01
3	3	0.1600E+02	0.0000E+01	0.0000E+01	0.0000E+01
4	3	0.2400E+02	0.0000E+01	0.0000E+01	0.0000E+01
5	3	0.3000E+02	0.0000E+01	0.0000E+01	0.0000E+01
6	3	0.3600E+02	0.0000E+01	0.0000E+01	0.0000E+01
7	3	0.4200E+02	0.0000E+01	0.0000E+01	0.0000E+01
8	3	0.4600E+02	0.0000E+01	0.0000E+01	0.0000E+01
9	3	0.5000E+02	0.0000E+01	0.0000E+01	0.0000E+01
10	3	0.5400E+02	0.0000E+01	0.0000E+01	0.0000E+01
11	3	0.5800E+02	0.0000E+01	0.0000E+01	0.0000E+01
12	3	0.6000E+02	0.0000E+01	0.0000E+01	0.0000E+01
13	3	0.6200E+02	0.0000E+01	0.0000E+01	0.0000E+01
14	3	0.6400E+02	0.0000E+01	0.0000E+01	0.0000E+01
15	3	0.6600E+02	0.0000E+01	0.0000E+01	0.0000E+01
16	3	0.6700E+02	0.0000E+01	0.0000E+01	0.0000E+01
17	3	0.6800E+02	0.0000E+01	0.0000E+01	0.0000E+01
18	3	0.6850E+02	0.0000E+01	0.0000E+01	0.0000E+01
19	3	0.6900E+02	0.0000E+01	0.0000E+01	0.0000E+01
20	3	0.6930E+02	0.0000E+01	0.0000E+01	0.0000E+01
21	3	0.6975E+02	0.0000E+01	0.0000E+01	0.0000E+01
22	3	0.6995E+02	0.0000E+01	0.0000E+01	0.0000E+01
23	3	0.0000E+01	0.8000E+01	0.0000E+01	0.0000E+01
24	0	0.8000E+01	0.8000E+01	0.0000E+01	0.0000E+01
25	0	0.1600E+02	0.8000E+01	0.0000E+01	0.0000E+01
26	0	0.2400E+02	0.8000E+01	0.0000E+01	0.0000E+01
27	0	0.3000E+02	0.8000E+01	0.0000E+01	0.0000E+01
28	0	0.3600E+02	0.8000E+01	0.0000E+01	0.0000E+01
29	0	0.4200E+02	0.8000E+01	0.0000E+01	0.0000E+01
30	0	0.4600E+02	0.8000E+01	0.0000E+01	0.0000E+01
31	0	0.5000E+02	0.8000E+01	0.0000E+01	0.0000E+01
32	0	0.5400E+02	0.8000E+01	0.0000E+01	0.0000E+01
33	0	0.5800E+02	0.8000E+01	0.0000E+01	0.0000E+01
34	0	0.6000E+02	0.8000E+01	0.0000E+01	0.0000E+01
35	0	0.6200E+02	0.8000E+01	0.0000E+01	0.0000E+01
36	0	0.6400E+02	0.8000E+01	0.0000E+01	0.0000E+01
37	0	0.6600E+02	0.8000E+01	0.0000E+01	0.0000E+01
38	0	0.6700E+02	0.8000E+01	0.0000E+01	0.0000E+01
39	0	0.6800E+02	0.8000E+01	0.0000E+01	0.0000E+01
40	0	0.6850E+02	0.8000E+01	0.0000E+01	0.0000E+01
41	0	0.6900E+02	0.8000E+01	0.0000E+01	0.0000E+01
42	0	0.6930E+02	0.8000E+01	0.0000E+01	0.0000E+01
43	0	0.6975E+02	0.8000E+01	0.0000E+01	0.0000E+01
44	1	0.6995E+02	0.8000E+01	0.0000E+01	0.0000E+01
45	3	0.0000E+01	0.1600E+02	0.0000E+01	0.0000E+01
46	0	0.8000E+01	0.1600E+02	0.0000E+01	0.0000E+01
47	0	0.1600E+02	0.1600E+02	0.0000E+01	0.0000E+01
48	0	0.2400E+02	0.1600E+02	0.0000E+01	0.0000E+01
49	0	0.3000E+02	0.1600E+02	0.0000E+01	0.0000E+01
50	0	0.3600E+02	0.1600E+02	0.0000E+01	0.0000E+01
51	0	0.4200E+02	0.1600E+02	0.0000E+01	0.0000E+01
52	0	0.4600E+02	0.1600E+02	0.0000E+01	0.0000E+01
53	0	0.5000E+02	0.1600E+02	0.0000E+01	0.0000E+01
54	0	0.5400E+02	0.1600E+02	0.0000E+01	0.0000E+01
55	0	0.5800E+02	0.1600E+02	0.0000E+01	0.0000E+01
56	0	0.6000E+02	0.1600E+02	0.0000E+01	0.0000E+01

597	0	0.2400E+02	0.6100E+02	0.0000E+01	0.0000E+01
598	0	0.3000E+02	0.6100E+02	0.0000E+01	0.0000E+01
599	0	0.3600E+02	0.6100E+02	0.0000E+01	0.0000E+01
600	0	0.4200E+02	0.6100E+02	0.0000E+01	0.0000E+01
601	0	0.4600E+02	0.6100E+02	0.0000E+01	0.0000E+01
602	0	0.5000E+02	0.6100E+02	0.0000E+01	0.0000E+01
603	0	0.5400E+02	0.6100E+02	0.0000E+01	0.0000E+01
604	0	0.5800E+02	0.6100E+02	0.0000E+01	0.0000E+01
605	0	0.6000E+02	0.6100E+02	0.0000E+01	0.0000E+01
606	0	0.6200E+02	0.6100E+02	0.0000E+01	0.0000E+01
607	0	0.6400E+02	0.6100E+02	0.0000E+01	0.0000E+01
608	0	0.6600E+02	0.6100E+02	0.0000E+01	0.0000E+01
609	0	0.6700E+02	0.6100E+02	0.0000E+01	0.0000E+01
610	0	0.6800E+02	0.6100E+02	0.0000E+01	0.0000E+01
611	0	0.6850E+02	0.6100E+02	0.0000E+01	0.0000E+01
612	0	0.6900E+02	0.6100E+02	0.0000E+01	0.0000E+01
613	0	0.6930E+02	0.6100E+02	0.0000E+01	0.0000E+01
614	0	0.6975E+02	0.6100E+02	0.0000E+01	0.0000E+01
615	1	0.7000E+02	0.6100E+02	0.0000E+01	0.0000E+01

INPUT TABLE 4.. ELEMENT DATA

	GLOBAL INDICES OF ELEMENT NODES				
ELEMENT	1	2	3	4	MATERIAL
1	1	2	24	23	2
2	2	3	25	24	2
3	3	4	26	25	2
4	4	5	27	26	2
5	5	6	28	27	2
6	6	7	29	28	2
7	7	8	30	29	2
8	8	9	31	30	2
9	9	10	32	31	2
10	10	11	33	32	2
11	11	12	34	33	2
12	12	13	35	34	2
13	13	14	36	35	2
14	14	15	37	36	2
15	15	16	38	37	2
16	16	17	39	38	2
17	17	18	40	39	2
18	18	19	41	40	2
19	19	20	42	41	2
20	20	21	43	42	2
21	21	22	44	43	2
22	23	24	46	45	2
23	24	25	47	46	2
24	25	26	48	47	2
25	26	27	49	48	2
26	27	28	50	49	2
27	28	29	51	50	2
28	29	30	52	51	2
29	30	31	53	52	2
30	31	32	54	53	2
31	32	33	55	54	2
32	33	34	56	55	2
33	34	35	57	56	2
34	35	36	58	57	2
35	36	37	59	58	2
36	37	38	60	59	2
37	38	39	61	60	2
38	39	40	62	61	2
39	40	41	63	62	2
40	41	42	64	63	2
41	42	43	65	64	2
42	43	44	66	65	2
43	45	46	68	67	2
44	46	47	69	68	2
45	47	48	70	69	2
46	48	49	71	70	2
47	49	50	72	71	2
48	50	51	73	72	2
49	51	52	74	73	2
50	52	53	75	74	2
51	53	54	76	75	2
52	54	55	77	76	2
53	55	56	78	77	2
54	56	57	79	78	2
55	57	58	80	79	2
56	58	59	81	80	2

↓etc.

537	563	564	586	585	3
538	564	565	587	586	3
539	565	566	588	587	3
540	566	567	589	588	3
541	567	568	590	589	3
542	568	569	591	590	3
543	569	570	592	591	3
544	570	571	593	592	3
545	572	573	595	594	3
546	573	574	596	595	3
547	574	575	597	596	3
548	575	576	598	597	3
549	576	577	599	598	3
550	577	578	600	599	3
551	578	579	601	600	3
552	579	580	602	601	3
553	580	581	603	602	3
554	581	582	604	603	3
555	582	583	605	604	3
556	583	584	606	605	3
557	584	585	607	606	3
558	585	586	608	607	3
559	586	587	609	608	3
560	587	588	610	609	3
561	588	589	611	610	3
562	589	590	612	611	3
563	590	591	613	612	3
564	591	592	614	613	3
565	592	593	615	614	3

INPUT TABLE 5.. SURFACE LOADING DATA

SURFACE LOAD INTENSITIES AT NODES

NODE I	NODE J	XI	XJ	YI	YJ
264	286	0.1129E+04	0.9277E+03	0.0000E+01	0.0000E+01
286	308	0.9277E+03	0.7659E+03	0.0000E+01	0.0000E+01
308	330	0.7659E+03	0.6851E+03	0.0000E+01	0.0000E+01
330	352	0.6851E+03	0.6043E+03	0.0000E+01	0.0000E+01
352	374	0.6043E+03	0.5235E+03	0.0000E+01	0.0000E+01
374	396	0.5235E+03	0.4428E+03	0.0000E+01	0.0000E+01
396	418	0.4428E+03	0.3418E+03	0.0000E+01	0.0000E+01

XXY(1)= 69.7500

XXY(2)= 53.2500

XXY(3)= 69.9500

XXY(4)= 53.2500

XXY(5)= 70.0000

XXY(6)= 53.7500

XXY(7)= 69.7500

XXY(8)= 53.7500

XXY(9)= 69.7500

XXY(10)= 53.5000

SMU ETA = 296296. 1.60000

LP (1)= 833

LP (2)= 834

LP (3)= 835

LP (4)= 836

LP (5)= 921

LP (6)= 922

LP (7)= 919

LP (8)= 920

LP (9)= 877

LP (10)= 878

EK(1)= 417700. AK(833, 1)= 0.228690E+07

EK(2)= 184875. AK(833, 2)= -62038.5

EK(4)= -588078. AK(833, 3)= -0.147536E+07

EK(7)=	684789.	AK(833, 4)=	586023.
EK(11)=	-837088.	AK(833, 89)=	-837088.
EK(16)=	299415.	AK(833, 90)=	299415.
EK(22)=	-59503.0	AK(833, 87)=	-59503.0
EK(29)=	-212898.	AK(833, 88)=	-212898.
EK(37)=	45405.0	AK(833, 45)=	-16180.3
EK(46)=	-174474.	AK(833, 46)=	-75708.6
EK(3)=	957870.	AK(834, 1)=	0.274957E+07
EK(5)=	-215972.	AK(834, 2)=	-117207.
EK(8)=	877590.	AK(834, 3)=	766150.
EK(12)=	-358996.	AK(834, 88)=	-358996.
EK(17)=	36150.5	AK(834, 89)=	36150.5
EK(23)=	5510.71	AK(834, 86)=	5510.71
EK(30)=	3410.25	AK(834, 87)=	3410.25
EK(38)=	-44951.4	AK(834, 44)=	-143717.
EK(47)=	-52300.7	AK(834, 45)=	-800582.
EK(6)=	968673.	AK(835, 1)=	0.192701E+07
EK(9)=	-0.123052E+07	AK(835, 2)=	-983604.
EK(13)=	0.150160E+07	AK(835, 87)=	0.150160E+07
EK(18)=	-672270.	AK(835, 88)=	-672270.
EK(24)=	62758.4	AK(835, 85)=	62758.4
EK(31)=	382421.	AK(835, 86)=	382421.
EK(39)=	-203353.	AK(835, 43)=	-203353.
EK(48)=	338999.	AK(835, 44)=	338999.
EK(10)=	0.296001E+07	AK(836, 1)=	0.337935E+07
EK(14)=	-0.227816E+07	AK(836, 86)=	-0.227816E+07
EK(19)=	0.128738E+07	AK(836, 87)=	0.128738E+07
EK(25)=	-123993.	AK(836, 84)=	-123993.
EK(32)=	-835522.	AK(836, 85)=	-835522.
EK(40)=	409289.	AK(836, 42)=	409289.

```
EK(  49)=        -678742.     AK(836,  43)=        -678742.
EK(  15)=       0.304262E+07AK(921,   1)=       0.370452E+07
EK(  20)=      -0.136613E+07AK(921,   2)=      -0.161304E+07
EK(  21)=         994082.     AK(922,   1)=       0.143286E+07
EK(  26)=         17294.2     AK(919,   3)=        -538778.
EK(  27)=         92972.3     AK(919,   4)=         191738.
EK(  28)=         220480.     AK(919,   1)=       0.175314E+07
EK(  35)=        -4516.77     AK(919,   2)=         242397.
EK(  33)=         807875.     AK(920,   2)=         709109.
EK(  34)=        -649759.     AK(920,   3)=        -629988.
EK(  36)=         633420.     AK(920,   1)=       0.251987E+07
EK(  41)=        -694315.     AK(877,  45)=        -694315.
EK(  42)=         312595.     AK(877,  46)=         312595.
EK(  43)=        -6956.74     AK(877,  43)=        -68542.1
EK(  44)=        -186293.     AK(877,  44)=        -87527.6
EK(  45)=         380178.     AK(877,   1)=       0.121665E+07
EK(  54)=        -131997.     AK(877,   2)=        -131997.
EK(  50)=         565610.     AK(878,  44)=         565610.
EK(  51)=        -385751.     AK(878,  45)=        -385751.
EK(  52)=        -70180.5     AK(878,  42)=        -168946.
EK(  53)=         209317.     AK(878,  43)=        -538965.
EK(  55)=         316467.     AK(878,   1)=       0.197764E+07
NODE NOE MATYP XC,YC =    5  10   1     70.000          53.500
```

OUTPUT TABLE 1.. NODAL DISPLACEMENTS

NODE	U = X-DISP.	V = Y-DISP.
1	0.00000000E+01	0.00000000E+01
2	0.00000000E+01	0.00000000E+01
3	0.00000000E+01	0.00000000E+01
4	0.00000000E+01	0.00000000E+01
5	0.00000000E+01	0.00000000E+01
6	0.00000000E+01	0.00000000E+01
7	0.00000000E+01	0.00000000E+01
8	0.00000000E+01	0.00000000E+01
9	0.00000000E+01	0.00000000E+01
10	0.00000000E+01	0.00000000E+01
11	0.00000000E+01	0.00000000E+01
12	0.00000000E+01	0.00000000E+01
13	0.00000000E+01	0.00000000E+01
14	0.00000000E+01	0.00000000E+01
15	0.00000000E+01	0.00000000E+01
16	0.00000000E+01	0.00000000E+01
17	0.00000000E+01	0.00000000E+01
18	0.00000000E+01	0.00000000E+01
19	0.00000000E+01	0.00000000E+01
20	0.00000000E+01	0.00000000E+01
21	0.00000000E+01	0.00000000E+01
22	0.00000000E+01	0.00000000E+01
23	0.00000000E+01	0.00000000E+01
24	-0.29459278E-03	-0.28193387E-03
25	-0.44878650E-03	-0.43177822E-03
26	-0.51457460E-03	-0.58366282E-03
27	-0.51170654E-03	-0.68915919E-03
28	-0.47060586E-03	-0.78535081E-03
29	-0.40061687E-03	-0.86495271E-03
30	-0.34372909E-03	-0.90640712E-03
31	-0.28343639E-03	-0.93907456E-03
32	-0.22265075E-03	-0.96365586E-03
33	-0.16326207E-03	-0.98131581E-03
34	-0.13475132E-03	-0.98804972E-03
35	-0.10679104E-03	-0.99339968E-03
36	-0.79320687E-04	-0.99748519E-03
37	-0.52242535E-04	-0.10003954E-02
38	-0.38937255E-04	-0.10014255E-02
39	-0.25682929E-04	-0.10021573E-02
40	-0.19088827E-04	-0.10024125E-02
41	-0.12501123E-04	-0.10025926E-02
42	-0.85532066E-05	-0.10026646E-02
43	-0.26302938E-05	-0.10027219E-02
44	0.00000000E+01	-0.10027280E-02
45	0.00000000E+01	0.00000000E+01
46	-0.38157881E-03	-0.42538909E-03
47	-0.65292158E-03	-0.78945290E-03
48	-0.77454617E-03	-0.11485390E-02
49	-0.77187055E-03	-0.14035886E-02
50	-0.69960538E-03	-0.16307741E-02
51	-0.57774340E-03	-0.18103427E-02
52	-0.48162371E-03	-0.18977547E-02
53	-0.38343408E-03	-0.19608413E-02
54	-0.28984585E-03	-0.20030270E-02
55	-0.20482598E-03	-0.20293368E-02
56	-0.16618953E-03	-0.20385736E-02
57	-0.12975121E-03	-0.20456273E-02

↓ etc.

598	0.25433114E-02	-0.54546608E-02
599	0.25694593E-02	-0.68603169E-02
600	0.23651390E-02	-0.79864856E-02
601	0.20386126E-02	-0.84418006E-02
602	0.15607427E-02	-0.85685298E-02
603	0.91011823E-03	-0.82453191E-02
604	0.97091072E-04	-0.73450069E-02
605	-0.38923418E-03	-0.65925266E-02
606	-0.83608933E-03	-0.56247722E-02
607	-0.11483184E-02	-0.44416935E-02
608	-0.11743366E-02	-0.31315278E-02
609	-0.10270291E-02	-0.25424788E-02
610	-0.76199918E-03	-0.20472161E-02
611	-0.59469481E-03	-0.18627626E-02
612	-0.40683914E-03	-0.17251853E-02
613	-0.28889666E-03	-0.16680948E-02
614	-0.10311623E-03	-0.16194794E-02
615	0.00000000E+01	-0.16124230E-02

OUTPUT TABLE 2.. STRESSES AT ELEMENT CENTROIDS

ELEMENT	X	Y	SIGMA(X)	SIGMA(Y)	TAU(X,Y)	SIGMA(1)	SIGMA(2)	ANGLE
1	4.00	4.00	-4.0300E-01	-3.9773E-01	-1.2011E-01	-2.8023E-01	-5.2050E-01	-4.5629E+01
2	12.00	4.00	-4.8615E-01	-7.1928E-01	-1.8609E-01	-3.8313E-01	-8.2230E-01	-2.8969E+01
3	20.00	4.00	-5.5301E-01	-9.4870E-01	-2.3234E-01	-4.4569E-01	-1.0560E+00	-2.4793E+01
4	27.00	4.00	-6.1528E-01	-1.1472E+00	-2.4311E-01	-5.2091E-01	-1.2416E+00	-2.1215E+01
5	33.00	4.00	-6.6730E-01	-1.3045E+00	-2.3137E-01	-5.9216E-01	-1.3797E+00	-1.7993E+01
6	39.00	4.00	-7.1798E-01	-1.4445E+00	-2.0362E-01	-6.6481E-01	-1.4977E+00	-1.4636E+01
7	44.00	4.00	-7.5836E-01	-1.5438E+00	-1.7234E-01	-7.2221E-01	-1.5800E+00	-1.1847E+01
8	48.00	4.00	-7.8825E-01	-1.6074E+00	-1.4427E-01	-7.6358E-01	-1.6321E+00	-9.7018E+00
9	52.00	4.00	-8.1519E-01	-1.6586E+00	-1.1568E-01	-7.9961E-01	-1.6742E+00	-7.6693E+00
10	56.00	4.00	-8.3824E-01	-1.6981E+00	-8.7757E-02	-8.2938E-01	-1.7070E+00	-5.7681E+00
11	59.00	4.00	-8.5437E-01	-1.7225E+00	-6.7698E-02	-8.4913E-01	-1.7277E+00	-4.4325E+00
12	61.00	4.00	-8.6224E-01	-1.7344E+00	-5.4780E-02	-8.5881E-01	-1.7379E+00	-3.5798E+00
13	63.00	4.00	-8.6859E-01	-1.7439E+00	-4.2178E-02	-8.6657E-01	-1.7459E+00	-2.7523E+00
14	65.00	4.00	-8.7341E-01	-1.7510E+00	-2.9834E-02	-8.7240E-01	-1.7520E+00	-1.9448E+00
15	66.50	4.00	-8.7701E-01	-1.7555E+00	-2.0713E-02	-8.7653E-01	-1.7559E+00	-1.3500E+00
16	67.50	4.00	-8.7824E-01	-1.7572E+00	-1.4682E-02	-8.7799E-01	-1.7575E+00	-9.5667E-01
17	68.25	4.00	-8.7920E-01	-1.7584E+00	-1.0178E-02	-8.7908E-01	-1.7585E+00	-6.6318E-01
18	68.75	4.00	-8.7950E-01	-1.7588E+00	-7.1817E-03	-8.7944E-01	-1.7589E+00	-4.6790E-01
19	69.15	4.00	-8.7974E-01	-1.7591E+00	-4.7864E-03	-8.7971E-01	-1.7592E+00	-3.1184E-01
20	69.53	4.00	-8.7978E-01	-1.7592E+00	-2.5421E-03	-8.7977E-01	-1.7592E+00	-1.6561E-01
21	69.85	4.00	-8.7989E-01	-1.7593E+00	-5.9856E-04	-8.7989E-01	-1.7593E+00	-3.8997E-02
22	4.00	12.00	-6.8017E-01	-4.5820E-01	-1.6548E-01	-3.6993E-01	-7.6844E-01	-6.1924E+01
23	12.00	12.00	-6.2777E-01	-6.5927E-01	-1.6771E-01	-4.7507E-01	-8.1197E-01	-4.2318E+01
24	20.00	12.00	-6.1765E-01	-9.2396E-01	-2.0314E-01	-5.1640E-01	-1.0252E+00	-2.6493E+01
25	27.00	12.00	-6.1521E-01	-1.1513E+00	-2.0851E-01	-5.4366E-01	-1.2229E+00	-1.8939E+01
26	33.00	12.00	-6.2180E-01	-1.3347E+00	-1.9174E-01	-5.7351E-01	-1.3830E+00	-1.4138E+01
27	39.00	12.00	-6.3960E-01	-1.4924E+00	-1.5660E-01	-6.1175E-01	-1.5202E+00	-1.0084E+01
28	44.00	12.00	-6.6521E-01	-1.5997E+00	-1.1932E-01	-6.5021E-01	-1.6147E+00	-7.1630E+00
29	48.00	12.00	-6.9245E-01	-1.6633E+00	-8.9458E-02	-6.8427E-01	-1.6715E+00	-5.2208E+00
30	52.00	12.00	-7.2321E-01	-1.7107E+00	-6.2651E-02	-7.1925E-01	-1.7146E+00	-3.6160E+00
31	56.00	12.00	-7.5397E-01	-1.7441E+00	-4.0979E-02	-7.5227E-01	-1.7457E+00	-2.3660E+00
32	59.00	12.00	-7.7765E-01	-1.7640E+00	-2.8518E-02	-7.7683E-01	-1.7648E+00	-1.6548E+00
33	61.00	12.00	-7.8962E-01	-1.7731E+00	-2.1669E-02	-7.8914E-01	-1.7736E+00	-1.2616E+00
34	63.00	12.00	-7.9959E-01	-1.7803E+00	-1.5829E-02	-7.9934E-01	-1.7805E+00	-9.2447E-01
35	65.00	12.00	-8.0726E-01	-1.7855E+00	-1.0785E-02	-8.0714E-01	-1.7857E+00	-6.3156E-01
36	66.50	12.00	-8.1332E-01	-1.7894E+00	-7.3716E-03	-8.1326E-01	-1.7894E+00	-4.3269E-01
37	67.50	12.00	-8.1527E-01	-1.7907E+00	-5.1834E-03	-8.1524E-01	-1.7907E+00	-3.0447E-01
38	68.25	12.00	-8.1695E-01	-1.7917E+00	-3.5814E-03	-8.1694E-01	-1.7917E+00	-2.1051E-01
39	68.75	12.00	-8.1743E-01	-1.7920E+00	-2.5200E-03	-8.1742E-01	-1.7920E+00	-1.4815E-01
40	69.15	12.00	-8.1785E-01	-1.7923E+00	-1.6792E-03	-8.1784E-01	-1.7923E+00	-9.8732E-02
41	69.53	12.00	-8.1790E-01	-1.7923E+00	-8.9318E-04	-8.1789E-01	-1.7923E+00	-5.2518E-02
42	69.85	12.00	-8.1810E-01	-1.7925E+00	-2.0823E-04	-8.1810E-01	-1.7925E+00	-1.2245E-02
43	4.00	19.00	-7.6347E-01	-4.7406E-01	-2.0083E-01	-3.7123E-01	-8.6629E-01	-6.2888E+01
44	12.00	19.00	-7.1854E-01	-6.4419E-01	-2.1050E-01	-4.6761E-01	-8.9512E-01	-5.0008E+01
45	20.00	19.00	-6.5778E-01	-9.0472E-01	-2.3254E-01	-5.1797E-01	-1.0445E+00	-3.1017E+01
46	27.00	19.00	-6.1373E-01	-1.1639E+00	-2.2811E-01	-5.3145E-01	-1.2462E+00	-1.9834E+01
47	33.00	19.00	-5.8915E-01	-1.3760E+00	-1.9533E-01	-5.4333E-01	-1.4218E+00	-1.3202E+01

↓ etc.

ELEMENT	X	Y	SIGMA(X)	SIGMA(Y)	TAU(X,Y)	SIGMA(1)	SIGMA(2)	ANGLE
538	66.50	58.75	-1.2728E+01	4.9650E+00	7.0390E+01	6.7063E+01	-7.4826E+01	4.8582E+01
539	67.50	58.75	1.0436E+01	-1.3283E+01	6.8006E+01	6.7610E+01	-7.0456E+01	4.0054E+01
540	68.25	58.75	2.7765E+01	-2.9699E+01	5.7093E+01	6.2948E+01	-6.4882E+01	3.1643E+01
541	68.75	58.75	3.8928E+01	-3.8991E+01	4.4427E+01	5.9058E+01	-5.9121E+01	2.4376E+01
542	69.15	58.75	4.6020E+01	-4.5326E+01	3.1820E+01	5.6012E+01	-5.5317E+01	1.7433E+01
543	69.53	58.75	5.0431E+01	-4.8837E+01	1.8259E+01	5.3683E+01	-5.2089E+01	1.0099E+01
544	69.88	58.75	5.2578E+01	-5.0865E+01	4.8212E+00	5.2802E+01	-5.1089E+01	2.6627E+00
545	4.00	60.25	5.0753E+01	1.4270E+01	-4.6237E+00	5.1330E+01	1.3693E+01	-7.1116E+00
546	12.00	60.25	3.6270E+01	-1.8187E+00	-4.7763E-01	3.6276E+01	-1.8247E+00	-7.1834E-01
547	20.00	60.25	2.6229E+01	3.2224E-02	-2.0418E+00	2.6387E+01	-1.2596E-01	-4.4301E+00
548	27.00	60.25	1.5221E+01	-1.5222E-01	-1.9310E+00	1.5460E+01	-3.9106E-01	-7.0510E+00
549	33.00	60.25	3.4321E+00	2.0267E-01	-2.2143E+00	4.5579E+00	-9.2315E-01	-2.6950E+01
550	39.00	60.25	-1.0424E+01	-7.1816E-02	-2.4162E+00	4.6435E-01	-1.0960E+01	-7.7489E+01
551	44.00	60.25	-2.7063E+01	-8.9174E-01	-2.4098E+00	-6.7170E-01	-2.7283E+01	-8.4783E+01
552	48.00	60.25	-4.0146E+01	1.6554E-01	-3.2820E+00	4.3100E-01	-4.0412E+01	-8.5376E+01
553	52.00	60.25	-5.5168E+01	3.4740E-02	-3.5934E+00	2.6766E-01	-5.5401E+01	-8.6292E+01
554	56.00	60.25	-7.0142E+01	7.4205E-02	-2.6765E+00	1.7608E-01	-7.0244E+01	-8.7821E+01
555	59.00	60.25	-8.2451E+01	-8.2955E-01	9.9843E-01	-8.1734E-01	-8.2463E+01	8.9300E+01
556	61.00	60.25	-7.7362E+01	1.5862E+00	4.7301E+00	1.8685E+00	-7.7644E+01	8.6584E+01
557	63.00	60.25	-5.7162E+01	2.2114E+00	1.3690E+01	5.2162E+00	-6.0166E+01	7.7622E+01
558	65.00	60.25	-1.2926E+01	4.0496E+00	2.5963E+01	2.2877E+01	-3.1753E+01	5.4052E+01
559	66.50	60.25	3.5522E+01	2.9363E+00	3.0149E+01	5.3499E+01	-1.5040E+01	3.0806E+01
560	67.50	60.25	7.0942E+01	-2.2983E+00	2.9547E+01	8.1376E+01	-1.2732E+01	1.9449E+01
561	68.25	60.25	9.4457E+01	-5.8944E+00	2.4019E+01	9.9909E+01	-1.1347E+01	1.2790E+01
562	68.75	60.25	1.0719E+02	-8.0856E+00	1.8544E+01	1.1010E+02	-1.0995E+01	8.9175E+00
563	69.15	60.25	1.1428E+02	-9.7672E+00	1.3108E+01	1.1565E+02	-1.1137E+01	5.9663E+00
564	69.53	60.25	1.1937E+02	-1.0105E+01	7.5472E+00	1.1981E+02	-1.0543E+01	3.3249E+00
565	69.88	60.25	1.2090E+02	-1.0897E+01	2.0391E+00	1.2094E+02	-1.0929E+01	8.8613E-01

. . . STRAIN ENERGY W/O CKEL= 9.28372 . . .

```
NCKEL=  1
CKEL =    1

... STRESS INTENSIYY FACTOR ... 1
OPENING  MODE K1 =          -1066.60
SHEARING MODE K2 =           0.00000
CRACK TIP  XC =     70.0000     YC =     53.5000      AT MATERIAL   1
THE   5NODES = 417 418 461 460 439
STRAIN ENERGY =    0.425538
      * * * * * * * * * * * * * * * * * * * *

...TOTAL STRAIN ENERGY =       9.7092569    . . .
```

Crack Propagation Calculation Program

Figure B-2 shows the program flow diagram. The following is a brief description of the main program and each subroutine.

CRACK:

Main program. Sets values of necessary parameters and reads in necessary data. Iterates from problem to problem, reading in data specific to the problem and calling NVSC. Writes out modulus values, A, and n for each modulus condition considered.

NVSC: Calculates and applies crack increments. Computes N_f values for each increment. Computes N_f for each crack increment. Prints the base and overlay thicknesses and the modulus condition of the pavement being analyzed.

TRAPRLE:

Given the left and right limits of the crack increment, numerically integrates the Paris equation using the trapezoidal rule, producing N_f. Iterates until the percent difference is below 10^{-3} or to a limit of 15 iterations.

SIMPRLE:

Performs exactly as does TRAPRLE except that Simpson's rule is used for the numerical integration.



Figure B-2. Flow Diagram of Program for Solution of Paris Equation

PARIS:

Determines the value of K_I for a given value of (c/b) according to equation (6), Section I. Computes the integrand of equation (4), Section I, including the base thickness term. Paris is a function which returns as its value the above integrand.

Input Guide- The input parameters and formats are explained here.

BASIC PARAMETERS:

One Card: Format 2I5

cc 1-5 Nmodcon: The number of modulus conditions considered for the problem.

cc 6-10 K: A value of K = 0 indicates that the trapezoidal rule will be used. Any other 5 digit integer, normally 1, indicates that Simpson's rule will be used.

Nmodcon cards: Format 4F10.0

cc 1-10 Evalues(I,1): Modulus of elasticity of the base corresponding to modulus condition 1.

cc11-20 Evalues(I,2): Modulus of elasticity of the overlay corresponding to modulus condition 1

cc 21-30 AA(I): Values of the parameter A in the Paris equation corresponding to modulus condition 1.

cc 31-40 NN(I): Value of the parameter n in the Paris equation corresponding to modulus condition 1.

PROBLEM PARAMETERS:

One card per problem: Format 3I5

cc 1-5 Nprob: The problem number of the current problem. If the value is 0, execution of the program is halted.

cc 6-10 Base: Thickness of the base.

cc 11-15 Olay: Thickness of the overlay.

Nmodcon cards per problem: Format 6F10.0

cc 1-10 B_0: Coefficient B_0 in equation (6), Section I.

cc 11-20 B_1: Coefficient B_1 in equation (6), Section I.

cc 21-30 B_2: Coefficient B_2 in equation (6), Section I.

cc 31-40 B_3: Coefficient B_3 in equation (6), Section I.

cc 41-50 Left: Initial crack length for a pavement with given base and overlay thicknesses and modulus condition.

cc 51-60 Right: Final crack length for a pavement with given base and overlay thicknesses and modulus condition.

The computer code listing for the paris equation calculation scheme is given on the following pages.

```
      PROGRAM CRACK(INPUT,OUTPUT,TAPE5=INPUT,TAPE6=OUTPUT)
      IMPLICIT INTEGER (A-Z)
      REAL LEFT,RIGHT,TEST,AA(20),NN(20),EVALUES(20,2),OBASE
      REAL B0,B1,B2,B3
      COMMON/INTCON/ BASE,OLAY,B0,B1,B2,B3,AA,NN
      COMMON/PARAM/ IN,OUT,TEST,Z,EVALUES
      DATA TEST/0.001/,Z/15/,IN/5/,OUT/6/,OBASE/350000.0/
C
      READ (IN,100) NMODCON,K
C
      WRITE(OUT,500)
C
      DO 10 I=1,NMODCON
          READ (IN,200) EVALUES(I,1),EVALUES(I,2),AA(I),NN(I)
          WRITE(OUT,600) I,EVALUES(I,1),EVALUES(I,2),OBASE,AA(I),NN(I)
 10   CONTINUE
C
 20   READ (IN,300) NPROB,BASE,OLAY
C
      IF(NPROB.EQ.0) GO TO 40
C
      DO 30 I=1,NMODCON
          READ (IN,400) B0,B1,B2,B3,LEFT,RIGHT
          CALL NVSC(LEFT,RIGHT,I,K)
 30   CONTINUE
C
      IF(NPROB.NE.0) GO TO 20
C
 100  FORMAT(2I5)
 200  FORMAT(4F10.0)
 300  FORMAT(3I5)
 400  FORMAT(6F10.0)
 500  FORMAT(/////35X,'MODULUS',7X,'BASE',8X,'SUBGRDE',6X,'OVERLAY'/
     +34X,'CONDITION',5X,'MODULUS',2(6X,'MODULUS'),9X,'A',12X,'N'/30X,
     +6(4X,'----------'))
 600  FORMAT(34X,I5,8X,F9.1,6X,F6.1,6X,F8.1,4X,E9.4,6X,F5.2)
C
 40   STOP
      END
C
C
C
      SUBROUTINE TRAPRLE(CL,CR,MODCON,DNF,FLAG,DIFF)
      IMPLICIT REAL (A-Z)
      INTEGER YOMAMA,NDIV,I,J,MODCON,IN,OUT,Z
      LOGICAL FLAG
      COMMON/PARAM/ IN,OUT,TEST,Z,EVALUES
C
C
      FLAG=.FALSE.
      ODDSUM=0.0
      YOMAMA=0
      OLDVAL=0.0
      NDIV=4
C
C
      H=(CR-CL)/NDIV
      INTSUM=PARIS(CL+2*H,MODCON)
      ENDSUM=PARIS(CL,MODCON)+PARIS(CR,MODCON)
C
```

```
C
      DO 10 I=1,Z
         LIM=NDIV-1
C
         DO 20 J=1,LIM,2
            ODDSUM=ODDSUM+PARIS(CL+J*H,MODCON)
 20      CONTINUE
C
         INTSUM=INTSUM+ODDSUM
         NEWVAL=H/2*ENDSUM+H*INTSUM
         DIFF=ABS(NEWVAL-OLDVAL)/NEWVAL
C
C
         IF(DIFF.LT.TEST) THEN
            YOMAMA=1
            GO TO 30
         ELSE
            OLDVAL=NEWVAL
            NDIV=NDIV*2
            ODDSUM=0.0
            H=(CR-CL)/NDIV
         END IF
 10   CONTINUE
C
 30   IF(YOMAMA.EQ.0) THEN
         FLAG=.TRUE.
         DNF=NEWVAL
      ELSE
         DNF=NEWVAL
      END IF
C
C
      RETURN
      END
C
C
C
      REAL FUNCTION PARIS(X,E)
      IMPLICIT REAL (A-Z)
      INTEGER E,BASE,OUT
      DIMENSION AA(20),NN(20)
      COMMON/INTCON/ BASE,OLAY,B0,B1,B2,B3,AA,NN
      COMMON/PARAM/ IN,OUT,TEST,Z,EVALUES
C
      A=AA(E)
      N=NN(E)
      KI=B0+B1*X+B2*(X**2)+B3*(X**3)
      IF(KI.LE.0.0) THEN
         WRITE(OUT,100) X
         STOP
      END IF
      POWER=-N
      KN=KI**POWER
      PARIS=(KN/A)*BASE
C
C
 100  FORMAT(1X,'>>>>>>>>>>>',' KI IS NEGATIVE FOR C/B= ',F6.4)
C
C
 999  RETURN
```

```
      END
C
C
C
      SUBROUTINE NVSC(LEFT,RIGHT,MODCON,K)
      IMPLICIT REAL (A-Z)
      INTEGER NINC,I,OUT
      LOGICAL FLAG
      COMMON /PARAM/ IN,OUT
      COMMON /INTCON/ BASE,OLAY
C
C
      NF=0.0
      NINC=20
C
      DC=(RIGHT-LEFT)/NINC
      CL=LEFT
C
      WRITE(OUT,100) BASE,OLAY,MODCON
      WRITE(OUT,200)
C
      DO 10 I=1,NINC
          CR=CL+DC
          IF(K.EQ.0) THEN
              CALL TRAPRLE(CL,CR,MODCON,DNF,FLAG,DIFF)
          ELSE
              CALL SIMPRLE(CL,CR,MODCON,DNF,FLAG,DIFF)
          END IF
          NF=NF+DNF
C
          WRITE(OUT,300) CL,CR,DNF,NF
          IF(FLAG) THEN
              WRITE(OUT,400) DIFF
          END IF
          CL=CR
 10   CONTINUE
C
C
 100  FORMAT(/////42X,'DEPTH OF BASE.....',I5//42X,
     +'DEPTH OF OVERLAY.....',I5//42X,'MODULUS CONDITION....',
     +I5)
 200  FORMAT(///39X,'INITIAL',9X,'CURRENT',6X,'INCREMENTAL',7X,
     +'CURRENT'/33X,2(4X,' C/B  RATIO '),2(5X,'LOAD CYCLES')/
     +33X,4(4X,'------------'))
 300  FORMAT(30X,2(10X,F6.4),8X,E10.5,6X,E10.5)
 400  FORMAT(/35X,'>>>>>>>>>>>','ERROR: THE PRECEEDING LOAD',
     +' CYCLES INCREMENT DID'/35X,'>>>>>>>>>>>',6X,'NOT CONVERGE.',
     +' THE VALUE OF % DIFFERENCE'/35X,'>>>>>>>>>>>',6X,'AFTER 15',
     +' ITERATIONS IS ',E10.5)
C
C
      RETURN
      END
C
C
C
      SUBROUTINE SIMPRLE(CL,CR,MODCON,DNF,FLAG,DIFF)
      IMPLICIT REAL (A-Z)
      INTEGER YODADY,NDIV,I,J,MODCON,IN,OUT,Z
      LOGICAL FLAG
```

```
      COMMON/PARAM/ IN,OUT,TEST,Z
C
C
      FLAG=.FALSE.
      YODADY=0
      NDIV=4
C
      H=(CR-CL)/NDIV
      EVENS=PARIS(CL+2*H,MODCON)
      ODDS=PARIS(CL+H,MODCON)+PARIS(CL+3*H,MODCON)
      ENDSUM=PARIS(CL,MODCON)+PARIS(CR,MODCON)
      OLDVAL=H/3.0*(ENDSUM+4*ODDS+2*EVENS)
C
      DO 10 I=2,Z
          NDIV=2*NDIV
          H=(CR-CL)/NDIV
          EVENS=EVENS+ODDS
          ODDS=0.0
          LIM=NDIV-1
          DO 20 J=1,LIM,2
              ODDS=ODDS+PARIS(CL+J*H,MODCON)
 20       CONTINUE
          NEWVAL=H/3.0*(ENDSUM+4*ODDS+2*EVENS)
          DIFF=ABS(NEWVAL-OLDVAL)/NEWVAL
          IF(DIFF.LT.TEST) THEN
              YODADY=1
              GO TO 30
          ELSE
              OLDVAL=NEWVAL
          END IF
 10   CONTINUE
C
 30   IF(YODADY.EQ.0) THEN
          FLAG=.TRUE.
          DNF=NEWVAL
      ELSE
          DNF=NEWVAL
      END IF
C
      RETURN
      END
```

Sample Input for Crack Propagation Program- THe following pages contain a printout of the input data for the sample program.

```
 1      6     1
 2 1200000.0 4000.0     1.0E-10         2.0
 3 1200000.0 9000.0     1.0E-10         2.0
 4 800000.0  4000.0     1.0E-10         2.0
 5 800000.0  9000.0     1.0E-10         2.0
 6 400000.0  4000.0     1.0E-10         2.0
 7 400000.0  9000.0     1.0E-10         2.0
 8       1    16     0
 9 808.9672   6928.043   -22642.82 17098.41   0.0          1.0
10 687.1326   5742.7     -19189.89 14661.88   0.0          1.0
11 776.454    6547.792   -22345.7  17517.9    0.0          1.0
12 611.02611  5000.017   -16980.85 13073.25   0.0          1.0
13 633.8081   5223.816   -17649.63 13556.44   0.0          1.0
14 472.8754   3650.308   -12930.04 10141.79   0.0          1.0
15       2    12     0
16 1297.536   7693.483   -22383.32 14619.22   0.0          1.0
17 1019.034   5847.388   -17613.8  11676.7    0.0          1.0
18 1162.857   6804.254   -20087.0  13202.72   0.0          1.0
19 875.8471   4887.16    -15129.88 10145.02   0.0          1.0
20 916.8071   5163.552   -15845.97 10587.44   0.0          1.0
21 654.5362   3373.223   -11169.04 7681.451   0.0          1.0
22       3     8     0
23 2047.043   6567.108   -14172.16 5067.807   0.0          0.925977
24 1490.105   4544.518   -10815.35 4237.885   0.0          0.880402
25 1753.576   5513.253   -12415.28 4625.061   0.0          0.905503
26 1260.895   3666.674   -9340.74  3857.532   0.0          0.849451
27 1351.92    3600.485   -8792.111 3060.146   0.0          0.837093
28 938.921    2345.091   -6942.935 3093.236   0.0          0.784195
29       4     8     3
30 -394.5381 37465.05    -117437.1 105884.9   0.010901     1.0
31 -235.5056 26687.0     -84582.0  76535.6    0.009085     1.0
32 -280.6712 30515.79    -96126.81 87240.12   0.009479     1.0
33 -137.2445 20948.11    -66598.86 60381.99   0.006694     1.0
34 -112.6183 20547.46    -64805.32 59002.9    0.005580     1.0
35 -12.82105 13339.98    -42658.1  38802.09   0.000965     1.0
36       5     8     6
37 -247.4966 28694.99    -89707.74 81544.99   0.008870     1.0
38 -148.9915 21328.18    -67057.85 60936.81   0.007146     1.0
39 -153.3865 23050.09    -71954.05 65549.56   0.006799     1.0
40 -72.99951 16591.39    -52166.28 47507.98   0.004463     1.0
41 -35.03687 15331.1     -48342.45 44153.58   0.002303     1.0
42 17.19202  10486.71    -32985.49 30127.45   0.0          1.0
43       0
```

Sample Output for Crack Propagation Program- The following pages contain the output for the sample problem.

MODULUS CONDITION	BASE MODULUS	SUBGRDE MODULUS	OVERLAY MODULUS	A	N
1	1200000.0	4000.0	350000.0	.1000E-09	2.00
2	1200000.0	9000.0	350000.0	.1000E-09	2.00
3	800000.0	4000.0	350000.0	.1000E-09	2.00
4	800000.0	9000.0	350000.0	.1000E-09	2.00
5	400000.0	4000.0	350000.0	.1000E-09	2.00
6	400000.0	9000.0	350000.0	.1000E-09	2.00

DEPTH OF BASE..... 16

DEPTH OF OVERLAY..... 0

MODULUS CONDITION.... 1

INITIAL C/B RATIO	CURRENT C/B RATIO	INCREMENTAL LOAD CYCLES	CURRENT LOAD CYCLES
0.0000	.0500	.88171E+04	.88171E+04
.0500	.1000	.55496E+04	.14367E+05
.1000	.1500	.43884E+04	.18755E+05
.1500	.2000	.39863E+04	.22741E+05
.2000	.2500	.40022E+04	.26744E+05
.2500	.3000	.43572E+04	.31101E+05
.3000	.3500	.50935E+04	.36194E+05
.3500	.4000	.63598E+04	.42554E+05
.4000	.4500	.84512E+04	.51005E+05
.4500	.5000	.11886E+05	.62891E+05
.5000	.5500	.17455E+05	.80346E+05
.5500	.6000	.25903E+05	.10625E+06
.6000	.6500	.36316E+05	.14257E+06
.6500	.7000	.43316E+05	.18588E+06
.7000	.7500	.39819E+05	.22570E+06
.7500	.8000	.27747E+05	.25345E+06
.8000	.8500	.15880E+05	.26933E+06
.8500	.9000	.83164E+04	.27764E+06
.9000	.9500	.43036E+04	.28195E+06
.9500	1.0000	.22864E+04	.28423E+06

etc.

END

FILMED

5-86

DTIC